

(12) **United States Patent**
Biaggi-Labiosa et al.

(10) **Patent No.:** **US 10,294,099 B1**
(45) **Date of Patent:** **May 21, 2019**

(54) **TEMPLATED NANOSTRUCTURE SENSORS
AND METHODS OF MANUFACTURE**

(56) **References Cited**

U.S. PATENT DOCUMENTS

(71) Applicant: **The United States of America as
represented by the Administrator of
the National Aeronautics and Space
Administration**, Washington, DC (US)

6,194,066	B1	2/2001	Hoffman
7,211,143	B2	5/2007	Yang et al.
7,276,389	B2	10/2007	Kim et al.
7,306,828	B2	12/2007	Barrera et al.
7,355,216	B2	4/2008	Yang et al.
7,465,210	B2	12/2008	Kim et al.
7,592,039	B2	9/2009	Huang et al.
7,713,778	B2	5/2010	Li et al.
7,898,005	B2	3/2011	Yang et al.
2008/0054790	A1	3/2008	Kim et al.

(Continued)

(72) Inventors: **Azlin M. Biaggi-Labiosa**, Cleveland,
OH (US); **Gary W. Hunter**, Oberlin,
OH (US)

(73) Assignee: **The United States of America as
Represented by the Administrator of
National Aeronautics and Space
Administration**, Washington, DC (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 544 days.

(21) Appl. No.: **13/788,041**

(22) Filed: **Mar. 7, 2013**

OTHER PUBLICATIONS

Satishkumar, B. C., et al. "Synthesis of metal oxide nanorods using
carbon nanotubes as templates." *Journal of Materials Chemistry*
10.9 (2000): 2115-2119.*

(Continued)

Primary Examiner — Robert J Eom

(74) *Attorney, Agent, or Firm* — Robert H. Earp, III;
William M. Johnson

(57) **ABSTRACT**

A microsensor and its method of manufacture are disclosed
based on templated metal or metal oxide nanostructures. The
microsensor includes an electrode that in one embodiment
may be configured as a first sawtooth patterned electrode
having a series of first peaks and first valleys and a second
electrode that by be configured as a second sawtooth pat-
terned electrode having a series of second peaks and second
valleys where the second peaks generally align with the first
peaks of the first electrode. A plurality of templated metal or
metal oxide nanostructures connect on one side to the first
electrode and on another side to the second electrode, where
an electrical property of the microsensor changes in
response to exposure to an environment to be monitored.

13 Claims, 13 Drawing Sheets


Related U.S. Application Data

(60) Provisional application No. 61/614,583, filed on Mar.
23, 2012.

(51) **Int. Cl.**
B81C 1/00 (2006.01)

(52) **U.S. Cl.**
CPC **B81C 1/00341** (2013.01)

(58) **Field of Classification Search**
CPC B81C 1/00341
See application file for complete search history.



References Cited

2009/0017197	A1 *	1/2009	Zhang	G01N 33/5438 427/126.5
2009/0157165	A1	6/2009	Miller et al.	
2009/0213369	A1	8/2009	Lee et al.	
2009/0319032	A1	12/2009	Weber et al.	
2010/0006148	A1	1/2010	Zheng et al.	
2011/0168968	A1	7/2011	Yang et al.	
2011/0297541	A1 *	12/2011	Jayatissa	G01N 33/0052 204/406

Liu, Jun-feng, et al. "Vanadium pentoxide nanobelts: highly selective and stable ethanol sensor materials." *Advanced Materials* 17.6 (2005): 764-767.*

* cited by examiner




Figure 1




Figure 2




Figure 3




Figure 5




Figure 4





Figure 5b






Figure 7a




Figure 7b




Figure 7c




Figure 7d




Figure 7e




Figure 7f




Figure 8a




Figure 8b




Figure 9




Figure 10




Figure 11




Figure 12




Figure 13




Figure 14




Figure 15




Figure 16




Figure 17

TEMPLATED NANOSTRUCTURE SENSORS AND METHODS OF MANUFACTURE

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of U.S. Provisional Application No. 61/614,583 filed on Mar. 23, 2012.

ORIGIN OF THE INVENTION

The invention described herein was made by an employee of the United States Government and may be manufactured and used by or for the United States Government for United States Government purposes without the payment of any royalties thereon or therefore.

DESCRIPTION

Chemical sensors are used in a wide variety of applications, including environmental monitoring, fire detection, emissions monitoring, and health monitoring. The fabrication of chemical sensors involving nanostructured materials holds the potential for the development of sensor systems with unique properties and improved performance. Semiconducting metal oxides like tin oxide (SnO_2) have been shown to respond to relevant chemical species such as oxygen (O_2), carbon monoxide (CO), ethanol ($\text{C}_2\text{H}_5\text{OH}$), nitric oxides (NO_x), propylene (C_3H_6), and hydrogen (H_2). There are a number of advantages to improving the capabilities of sensor materials such as metal oxides. For example, gas sensors based on polycrystalline tin oxide offer advantages over current technologies for detecting reducing gases, such as low cost, long lifetime, and high selectivity and sensitivity. The sensing mechanism in semiconducting metal oxides relies on perturbations in surface conductivity induced by chemical reactions between target gases and oxygen species adsorbed onto the surface. For n-type semiconductors like SnO_2 , the adsorption of oxygen creates surface-acceptor sites that immobilize conduction band electrons from the near surface region creating a depletion layer. Reducing gases such as CO remove surface bound oxygen atoms releasing the immobilized electrons, thereby decreasing the thickness of the depletion layer and hence increasing its conductivity. In contrast, oxidizing gases (e.g. NO_2) further immobilize the conduction band electrons from the near surface region by creating additional surface-acceptor sites. This increases the thickness of the depletion layer and consequently, the conductivity decreases (in other words, resistance increases).

Moreover, the sensitivity of the sensing layer increases with decreasing grain size, therefore nanocrystalline metal oxides films exhibit high sensitivity. However, the processing and fabrication of nanostructures, such as nanotubes, nanowires, or other more complex geometries based on nanosystems, for sensor applications presently is limited in the ability to control the structural and morphological properties. In addition, one of the main drawbacks of semiconductor metal oxide based sensors is their high working temperature; the optimum operating temperature is usually at least 350-450° C. In general, we have found it is desirable to produce sensors which are small in size, easy to batch fabricate, are low in cost, and have low power consumption. We also sought to decrease the operational temperature of existing gas sensor systems to allow lower temperature operation as well as increased sensitivity and selectivity.

The accompanying drawings, which are incorporated in and constitute a part of the specification, illustrate various example systems, methods, and so on that illustrates various example embodiments of aspects of the invention. It will be appreciated that the illustrated element boundaries (e.g., boxes, groups of boxes, or other shapes) in the figures represent one example of the boundaries. One of ordinary skill in the art will appreciate that one element may be designed as multiple elements or that multiple elements may be designed as one element. An element shown as an internal component of another element may be implemented as an external component and vice versa. Furthermore, elements may not be drawn to scale.

DESCRIPTION OF DRAWINGS

FIG. 1 is a top plan view of a sensor according to an aspect of the disclosure.

FIG. 2 is a scanning electron microscope image of a microsensor.

FIG. 3 is a scanning electron microscope image of a templated SnO_2 nanorod between opposing electrode peaks.

FIG. 4 is a transmission electron microscope image of a carbon nanorod covered in a metal oxide.

FIG. 5A is a transmission electron microscope image of a templated SnO_2 nanorod.

FIG. 5B is a high resolution transmission electron microscope image of a templated SnO_2 nanorod.

FIGS. 6A-6D are sequential figures showing aspects of sensor fabrication.

FIGS. 7A-7F are comparison charts of templated sensor performance at varying temperatures.

FIGS. 8A-8B are comparison charts of sensor performance.

FIG. 9 is a chart of sensor performance.

FIG. 10 is chart comparing sensor performance at varying temperatures.

FIGS. 11-17 are charts showing sensor performance at varying temperatures.

As used herein, the term “templated” or “templated nanostructure” is intended to describe a resulting nanostructure formed from an initial template that has a morphological structure that is then coated by a higher temperature material. The initial template is sacrificed leaving essentially only the higher temperature material imprinted with the morphological structure of the template.

One example we considered was the sensitive detection of methane, which is a colorless and odorless flammable gas that occurs abundantly in nature as the chief constituent of natural gas. Methane gas is highly volatile and when mixed with air can cause explosions at higher concentrations due to its ready flammability. Thus, the development of a reliable and cost effective methane gas sensor was a promising problem for timely detection of its conspicuous presence in the environment around us. However, detection of methane at room temperature using a number of techniques is a particularly difficult challenge because it is a stable molecule. Efforts have been made to detect methane at room temperature using material systems such as single walled carbon nanotubes and multi walled carbon nano tubes (MW-CNTs) loaded with a catalyst such as palladium (Pd), and a Batron phosphorus-silicon microsensor, but they lack the temperature range and durability of materials such as metal oxides or metals.

A room temperature methane microsensor based on templated SnO_2 nanorods has been developed. The sensor may be fabricated by combining microfabrication techniques

with the alignment of the nanostructures such as described in the U.S. patent application Ser. No. 13/036,887 entitled "Processing of Nanostructured Devices using Microfabrication Techniques" assigned to the assignee of the present disclosure and incorporated herein by reference and used in the following description of the sensor element (but not sensor material(s)) fabrication. The templated SnO₂ nanorods may be synthesized using carbon nanotubes as templates. As will be more fully described below, we have here described a sensor that operated at room temperature and detection of 0.25% methane in air. Furthermore, the uniqueness of this templated SnO₂ nanorod sensor includes the fact that it has a wide operating temperature range for CH₄ detection (25-500° C.), in contrast with the other material systems described above. Although tested on methane, hydrogen and propylene, the microsensor is expected to perform in other gaseous environments including those with hydrocarbon gases, carbon monoxide, nitrogen oxides, nitrogen tetroxide, fluorines, chlorines, ammonia, hydrazine, formaldehyde and in aqueous environments. Moreover, other templates beyond carbon nanotubes may be substituted to achieve the desired template features of the remaining nanotubes and corresponding sensitivity. These include, but are not limited to, biological materials such as plants, cells, filtration materials, organic substrates, and other materials whose basic structure holds biological advantages, but have a limited temperature range before undergoing decomposition. Other approaches have used a basic template approach. For example, sacrificial fibers can be coated with a metal to achieve modified sensor surface areas, or ceramic surfaces can serve as a basic structure for etching, growth, or modification to produce metal structures. However, these approaches are not based inherently on imprinting the crystal structure or inherent morphological properties of the substrate for improved sensing capabilities. Further, other oxide materials known for their gas sensing capabilities beyond tin oxide may be considered for the application of this approach. These include, but are not limited to tungsten oxide, titanium dioxide, indium oxide, indium tin oxide, zirconia, zinc oxide, copper oxide and iron oxide. Further, this approach may also be extended into metals that are known for their gas sensing capabilities. These include, but are not limited to, platinum, palladium, nickel, gold, ruthenium, silver, and iridium.

In one aspect, existing nanostructures such as carbon nanotubes have a material structure which can be used advantageously in order to provide new sensor systems. In a method of manufacturing, a user may start with a nanostructure template such as a carbon nanotube. This template can then be coated by a metal or oxide material with higher temperature capabilities. Upon heating in air, the carbon nanotube template is burned off leaving only the metal or metal oxide coating that retains the form of the carbon nanotube template. The resulting structure has a combination of the crystal patterns and surface morphology of the carbon nanotube, combined with the material durability and high temperature sensing properties of the metal or metal oxide. Further, because of its porosity, both the interior and the exterior of this sensing structure are available for gas species detection. This in effect increases the surface area available for sensing.

The limited capability to control the structural and morphological properties of nanostructures constraints their use in the processing and fabrication for sensor applications. For example, fabrication of sensors based on metals or metal oxides typically takes place in a growth process that yields a single or multi-grained structure with a structure deter-

mined by the crystallographic properties of the oxide. The surface area and morphology of such metals or metal oxides are notably different than that of, for example, other materials such as carbon nanotubes. In contrast, carbon nanotubes are noted for their large surface area and reactivity due in part to the crystal structure and resultant morphology. In principle, there could be notable advantages in producing metal or metal oxide nanostructures with a surface area and morphology similar to that of carbon nanotubes. However, it is considerably challenging to fabricate metal or metal oxide nanostructures with the same advantageous surface area and morphology, and potentially sensing properties, as carbon nanotubes. In effect, given the challenges in growing metal oxides and other materials such as metals, controlling and designing the material structure and morphology is problematic. One fundamental problem being addressed is improving the control of the structural and morphological properties of metal oxide and metal nanostructures in order to produce improved sensor systems.

In one example shown at FIGS. 1-3, a room temperature methane (CH₄) microsensor **100** based on templated tin oxide nanotubes **110** has been developed. The sensor **100** was fabricated integrating microfabrication techniques with the alignment and connection of the nanostructures between opposed tips **122**, **124** of electrodes, **132**, **134**. As more completely discussed below, templated tin oxide nanorods **110** were fabricated using carbon nanotubes as templates. The sensor **100** has been operated at a room temperature and detection of 0.25% methane in air demonstrated. The room temperature methane microsensor has the advantages of low power consumption, no heating requirement, and only using a detector (not shown) for changes in the sensor, such as electrical changes in resistance or conductance between electrode pads **142**, **144**. The sensor is small in size, simple to batch fabricate and high in sensor yield, extremely low cost, and easy to use. Again, while tested on methane (CH₄), the microsensor is expected to perform in other gaseous environments and in aqueous environments. Moreover, other templates beyond carbon nanotubes may be substituted to achieve the desired template features of the remaining metal or metal oxide nanotubes. Finally, while the nanotube alignment between opposing saw-tooth elements of electrodes is illustrated, many other configurations are possible where the template nanotubes provide a connection between opposed electrodes. In one embodiment, it is the change in material properties enabling enhanced sensing capabilities that is desirable as opposed to a specific fabrication approach which makes contact with these nano structured materials.

Example

In one example, fabrication of a microsensor included four major steps: 1) synthesis of templated metal or metal oxide nanostructures using a sacrificial template; 2) deposition of electrodes onto an alumina substrate; 3) alignment of the nanostructures between the electrodes and 4) deposition of the top electrodes to bury the aligned nanostructures.

Templated SnO₂ nanorods were synthesized using multi-walled carbon nanotubes (MWCNT) as templates. First, 1.0 g of MWCNT obtained commercially from NanoLab was refluxed in 100 mL of 7.0 M HNO₃ for 12 hours at 120° C. to remove any impurities from the nanotubes and to create oxygen-containing functional groups on the nanotube surface that act as sites for the subsequent SnO₂ coating. 1.0 g of SnCl₂·2H₂O was dissolved in 40 mL of deionized water

and 0.25 mL of 38% HCl was added. Next, 10 mg of the purified MWCNT was added and the solution was sonicated for 20 minutes. Afterwards, the solution was stirred at room temperature for 2 hours and then rinsed with deionized water until the solution was neutral. At this point, SnO₂/MWCNT hybrid nanostructures are obtained. FIG. 4 illustrates a MWCNT covered with SnO₂ nanoparticles, 400. The SnO₂/MWCNT hybrid nanostructures were then calcinated at 350° C. for 3 hours and then heated at 700° C. for 5 minutes to burn off the MWCNT. FIG. 5A shows the templated SnO₂ nanostructures, 500, formed as nanorods. FIG. 5B shows a high resolution transmission electron microscope (HRTEM) image of the nanocrystals in the templated SnO₂ nanorod with the lattice spacing corresponding to the rutile structure of SnO₂.

After obtaining the templated SnO₂ nanorods, the challenge is to integrate the nanostructures into a micro/macro sensor. Usually doing this involves repeatability issues as well as poor control of the density of the nanomaterial. The basic ability to control the orientation and alignment of nanostructures on microstructures is still in an early stage of development although various groups have made significant progress on a range of materials. In our example, this has been overcome by fabricating the sensors using microfabrication techniques combined with the alignment of the nanostructures using dielectrophoresis (DEP). As illustrated in FIG. 6, alumina substrates were patterned with a sawtooth electrode pattern with contact pads through photolithography and 2500 Å of platinum was deposited by sputter deposition, FIG. 6A. The templated SnO₂ nanorods are added to a photoresist solution 602 which is coated onto the substrate with the patterned electrodes, FIG. 6B. Dielectrophoresis is then used by applying an alternate current, 604, with a frequency of 10 MHz and 10 V peak to peak, through the contact pads in the substrate to align the templated SnO₂ nanorods 606 between the sawtooth patterned electrodes, FIGS. 6C and 6D. Afterwards, a top platinum electrode is patterned through photolithography and sputter deposited on top of the bottom platinum electrode. This way the templated SnO₂ nanorods are buried between the bottom and top electrodes.

The methane microsensor described has a variety of advantages over other room temperature methane sensors in the simple synthesis of the sensing material with a stable metal oxide material, and over high temperature methane sensors in many aspects, especially in power consumption (no heating, only an amperometer is needed). Other advantages include miniature size, low weight and cost, and convenience of use. This particular sensor example has other desirable attributes. First, is the use of microfabrication processes to fabricate micro-sized sensor electrodes. The application of photolithography and sputtering processing to fabricate sensor electrodes enables the sensor to have small sizes. The electrodes shown in FIGS. 2 and 3 comprise sawtooth patterned electrodes which would be very difficult to make with other processes. The electrodes are batch fabricated with low cost, high yield, and robust structure. However, one attribute is the use of templated SnO₂ nanorods and the design of the sensor structure that yields unique sensor properties.

The templated SnO₂ nanorods that were used as the sensing material are composed of a network of SnO₂ nanocrystals. When the SnO₂ crystallite size is comparable to or less than 2 L (~6 nm), where L is the depth of the depletion layer, the sensitivity can be greatly increased because the sensitivity of the sensor's transducer function is proportional to the surface to volume ratio of the sensor material. The size

of the nanocrystals on the templated SnO₂ nanorods was measured to be on average ~5.0 nm.

When the templated SnO₂ nanorods described are used as the sensing material, because of their porous nature as illustrated in FIG. 5A, they become more sensitive than non-templated SnO₂ nanorods, nanobelts, nanocrystalline thin films or other nanostructures because gas molecules can freely pass into and out of the templated nanorod through the pores and interact with the outer as well as the inner surface of the nanorod. As a consequence, there is a larger effective area and the sensitivity at room temperature is greatly increased. However, the increase in active surface area and consequently, gas diffusion does not necessarily translate into a proportional increase in sensitivity. There are other factors involved in the transduction of the analyte gas/surface reactions into an electrical conductance change: 1) electrode/SnO₂ nanotube contact, 2) nanocrystal organization within the SnO₂ nanotube and 3) electrical and surface properties of the electrodes.

Furthermore, by having sawtooth patterned electrodes on the sensor structure, the use of DEP to align the nanostructures becomes more feasible. DEP exploits the dielectric difference between the solvent and the nanostructures in the solvent to induce temporary dipoles that align with the imposed electric field. Because of the geometry of the electrodes, the electric field is greater at the tips of the sawtooth patterned electrodes which accounts for the preferential alignment of the nanotubes between the tips of opposing sawtooth electrodes. The approach used also allows for the ability to bury the nanostructure by performing a second electrode deposition on top of the aligned nanostructure, as described previously, allowing improved electrical contact.

A set of comparison tests were conducted comparing five different types of sensors:

Sensors formed from multiwall carbon nanotubes (listed as MWCNT).

Sensors formed from single wall carbon nanotubes (listed as SWCNT).

Sensors formed from hybrid multiwall carbon nanotubes coated in SnO₂.

Sensors formed from hybrid single wall carbon nanotubes coated in SnO₂.

Sensors formed from templated SnO₂ nanotubes.

All sensors were tested for 0.5% H₂ and 0.5% CH₄ in air at 25° C., 100° C., 200° C. and 300° C. As can be seen from in Table 1 the templated SnO₂ nanotube sensors had improved sensitivity in all testing conditions for both gasses. The values given in the table are the ratio of the sensor response to the reactant gas to that of its response in air.

TABLE 1

Structure	Sensor target	25° C.	100° C.	200° C.	300° C.
SWCNT	H ₂	1.225	N-M	1.066	1.095
	CH ₄	N-M	N-M	1.021	1.042
MWCNT	H ₂	1.0037	N-M	N-M	N-M
	CH ₄	N-R	N-R	N-R	N-R
SnO ₂ /MWCNT	H ₂	1.089	N-M	N-M	N-M
	CH ₄	N-R	N-R	1.001	1.001
SnO ₂ /SWCNT	H ₂	1.27	N-M	1.023	1.098
	CH ₄	N-M	N-R	1.022	1.026
Templated SnO ₂ Nanotube	H ₂	4.27	6.69	2.38	17.15
	CH ₄	1.34	1.18	1.24	3.65

N-M = Not measurable

N-R = No response

The sensor can be tested using the amperometric mode, by applying a voltage between the electrodes and measuring the current between them. In one example, FIG. 7 shows Current vs. Time curves were taken at different operating temperatures (25-500° C.) for sensors using templated SnO₂ nanorods as the sensing material for response to 0.25% CH₄ at the different temperatures where all measurements were taken with an applied voltage of 1.0 V and using air as the baseline gas. Shaded areas indicate “exposure” and correspond to the times of CH₄ gas exposure. As it can be seen, the templated SnO₂ nanorod sensor showed a measurable response to 0.25% CH₄ at room temperature (FIG. 7A) and continued response throughout the test up to 500° C. (FIG. 7F). In addition, as it can be appreciated in FIG. 7, the baseline at the different temperatures remains reasonably stable throughout the tests.

FIG. 8 shows a comparison test of a templated, porous SnO₂ nanorod sensor (FIG. 8A) and an alternative sensor structure using solid (non-templated) SnO₂ nanobelts without using the carbon nanotube-SnO₂ imprinting approach (FIG. 8B). Both Figures show Current vs. Time curves for 0.25% CH₄ in air at 25° C. and 1.0V. As can be seen, the non-templated sensor does not appear to show a usable response to CH₄ at room temperature.

FIG. 9 shows a sensor response curve to 0.25% CH₄ in air at 25° C. and 1.0V after approximately 190 hours of continuous testing of the templated SnO₂ nanorod sensor, cycling back and forth between the different temperatures. The curve shows an improved response to CH₄ at room temperature with little change in the baseline when compared with the previous results, thus establishing the sensor’s long-term stability.

FIG. 10 shows a templated SnO₂ nanotube sensor performance over time spaced exposures to 0.5% H₂ (during minutes 5-10) and 0.5% CH₄ (during minutes 18-26) in air at temperatures varying from 25° C. to 400° C.

FIGS. 11 and 12 show a templated SnO₂ nanotube sensor performance over time spaced exposures to C₃H₆ sensor in air at temperatures varying from 25° C. to 400° C. at varying scales.

FIGS. 13 and 17 show the templated SnO₂ nanotube sensor performance of FIGS. 11 and 12 over time spaced exposures to C₃H₆ sensor in air at temperatures varying from 25° C. to 400° C. at varying scales.

While the systems, methods, and so on have been illustrated by describing examples, and while the examples have been described in considerable detail, it is not the intention of the applicants to restrict or in any way limit the scope of the appended claims to such detail. It is, of course, not possible to describe every conceivable combination of components or methodologies for purposes of describing the systems, methods, and so on provided herein. Specific applications include toxic gas monitoring, explosive gas monitoring, detection of biological agents, and detection of biological molecules of interest such as cells, viruses, or proteins. A range of species are of interest to the scientific community and industry. One example can be found at http://www.nasa.gov/centers/johnson/pdf/485930main_SMACsGuidelines.pdf Additional advantages and modifications will readily appear to those skilled in the art. Therefore, the invention, in its broader aspects, is not limited to the specific details, the representative apparatus, and illustrative examples shown and described. Accordingly, departures may be made from such details without departing from the spirit or scope of the applicants’ general inventive concept. Thus, this application is intended to embrace alterations, modifications, and variations that fall within the scope of the

appended claims. Furthermore, the preceding description is not meant to limit the scope of the invention. Rather, the scope of the invention is to be determined by the appended claims and their equivalents. For example, although we describe sacrificing the “template” with high temperatures, one could also sacrifice with pressure or chemical solutions resulting in the templated nanostructure described. Moreover, other templates may be identified and selected for sensitivity to other desirable substances to test for in an air or liquid environment. Accordingly, the preceding description is not meant to limit the scope of the invention. Rather, the scope of the invention is to be determined by the appended claims and their equivalents.

As used herein, “connection” or “connected” means both directly, that is, without other intervening elements or components, as well as indirectly, that is, with another component or components arranged between the items identified or described as being connected. To the extent that the term “includes” or “including” is employed in the detailed description or the claims, it is intended to be inclusive in a manner similar to the term “comprising” as that term is interpreted when employed as a transitional word in a claim. Furthermore, to the extent that the term “or” is employed in the claims (e.g., A or B) it is intended to mean “A or B or both”. When the applicants intend to indicate “only A or B but not both” then the term “only A or B but not both” will be employed. Similarly, when the applicants intend to indicate “one and only one” of A, B, or C, the applicants will employ the phrase “one and only one”. Thus, use of the term “or” herein is the inclusive, and not the exclusive use. See, Bryan A. Garner, *A Dictionary of Modern Legal Usage* 624 (2d. Ed. 1995).

The invention claimed is:

1. A method of manufacturing a templated nanostructure microsensor, the method comprising:

providing a carbon-based template material with morphological properties usable in sensing a detectable material;

coating the carbon-based template material with a precipitate coating forming a combined structure such that the morphological properties of the carbon-based template material are imprinted in an interior surface of a precipitate coating having a crystallite size, wherein the precipitate coating comprises a metal oxide precipitate, the metal oxide selected from the group consisting of: tin tungsten oxide, titanium dioxide, indium oxide, indium tin oxide, zirconia, zinc oxide, copper oxide and iron oxide;

heat treating the combined structure in an environment containing oxygen such that the carbon-based template material is sacrificed leaving the precipitate coating having the interior surface imprinted with the morphological properties;

connecting physically spaced electrodes with nanostructures of the precipitate coating; and

depositing an upper electrode onto the physically spaced electrodes to bury points of contact between the physically spaced electrodes and the nanostructures;

wherein the morphological properties imprinted on the interior surface of the precipitate coating are used as a sensor via a depletion layer of the precipitate coating, wherein the crystallite size is less than twice a depth of the depletion layer of the precipitate coating.

2. The method as set forth in claim 1, further comprising detecting a change in an electrical property between the connected physically spaced electrodes at a temperature in the range of 25° C. and 600° C.

9

3. The method as set forth in claim 2, where the change in the electrical property indicates presence of the detectable material.

4. The method as set forth in claim 3, where the detectable material comprises hydrocarbon-based molecules, hydrazine, formaldehyde, oxidizers, nitrogen oxides, nitrogen tetraoxides, fluorines, chlorines, and ammonia.

5. The method as set forth in claim 3, where the detectable material comprises biological molecules in an aqueous solution.

6. The method as set forth in claim 1, wherein the physically spaced electrodes are patterned and aligned with one another.

7. The method as set forth in claim 6, further comprising, prior to depositing the upper electrode, aligning the nanostructures with patterns of the physically spaced electrodes via application of an electric field to the physically spaced electrodes.

8. The method as set forth in claim 7, wherein the patterns of the physically spaced electrodes comprise sawtooth patterns and the nanostructures are aligned between tips of the sawtooth patterns.

9. The method as set forth in claim 1, wherein the detectable material is a reducing gas.

10. The method as set forth in claim 1, wherein the carbon-based template comprises multiwall carbon nanotubes.

11. The method as set forth in claim 1, wherein the carbon-based template comprises single wall carbon nanotubes.

12. The method as set forth in claim 1, wherein the crystallite size is approximately 5 nanometers.

10

13. A method of manufacturing a templated nanostructure microsensor, the method comprising:

providing a carbon-based template material having a surface area usable in sensing a detectable material;

coating the carbon-based template material with a precipitate coating having a crystallite size, thereby forming a combined structure such that the surface area of the carbon-based template material is identically imprinted in the precipitate coating, wherein the precipitate coating comprises a metal oxide precipitate, the metal oxide selected from the group consisting of: tin oxide, tungsten oxide, titanium dioxide, indium oxide, indium tin oxide, zirconia, zinc oxide, copper oxide and iron oxide;

heat treating the combined structure in an environment containing oxygen such that the carbon-based template material is sacrificed leaving the precipitate coating having the identical surface area imprint of the carbon-based template material;

connecting separate electrodes with nanostructures of the precipitate coating; and

depositing an upper electrode onto the separate electrodes to bury points of contact between the separate electrodes and the nanostructures,

wherein the identical surface area imprint of the carbon-based template material is used as a sensor via a depletion layer of the precipitate coating, wherein the crystallite size is less than twice a depth of the depletion layer of the precipitate coating.

* * * * *