



US011173461B2

(12) **United States Patent**
Ye et al.

(10) **Patent No.:** **US 11,173,461 B2**
(45) **Date of Patent:** **Nov. 16, 2021**

(54) **FABRICATING STRUCTURED PARTICLES THROUGH RAPID HARDENING AND TAILORED COLLECTION METHODS**

(71) Applicants: **LAWRENCE LIVERMORE NATIONAL SECURITY, LLC**, Livermore, CA (US); **PURDUE RESEARCH FOUNDATION**, West Lafayette, IN (US)

(72) Inventors: **Congwang Ye**, Livermore, CA (US); **Roger D. Aines**, Livermore, CA (US); **Sarah E. Baker**, Dublin, CA (US); **Caitlyn Christian Cook**, Livermore, CA (US); **Eric B. Duoss**, Dublin, CA (US); **Joshua D. Kuntz**, Livermore, CA (US); **Elaine Lee**, Brooklyn, NY (US); **James S. Oakdale**, Castro Valley, CA (US); **Andrew J. Pascall**, Livermore, CA (US); **Joshuah K. Stolaroff**, Oakland, CA (US); **Marcus A. Worsley**, Hayward, CA (US); **Carlos J. Martinez**, West Lafayette, IN (US)

(73) Assignees: **Lawrence Livermore National Security, LLC**, Livermore, CA (US); **Purdue Research Foundation**, West Lafayette, IN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 346 days.

(21) Appl. No.: **15/928,522**

(22) Filed: **Mar. 22, 2018**

(65) **Prior Publication Data**
US 2019/0291067 A1 Sep. 26, 2019

(51) **Int. Cl.**
B01J 2/04 (2006.01)
B01J 13/14 (2006.01)

(52) **U.S. Cl.**
CPC **B01J 2/04** (2013.01); **B01J 13/14** (2013.01)

(58) **Field of Classification Search**
CPC B01J 13/04
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,599,627 B2 *	7/2003	Yeo		A61P 43/00	428/402.21
8,945,279 B2	2/2015	Aines et al.			
2002/0054912 A1	5/2002	Kim et al.			
2006/0071357 A1 *	4/2006	Pilon		A61K 9/5089	264/4

(Continued)

OTHER PUBLICATIONS

Dubey et al., "Microencapsulation Technology and Applications," Defense Science Journal, vol. 59, No. 1, 2009, pp. 82-95.

Primary Examiner — Galen H Hauth


Assistant Examiner — Asha A Thomas

(74) *Attorney, Agent, or Firm* — Eddie E. Scott

(57) **ABSTRACT**

Fabrication of functional polymer-based particles by cross-linking UV-curable polymer drops in mid-air and collecting crosslinked particles in a solid container, a liquid suspension, or an air flow. The particles can contain different phases in the form or layered structures that contain one to multiple cores, or structures that are blended with dissolved or emulsified smaller domains. A curing system produces ultraviolet rays that are directed onto the particles in the jet stream from one side. A reflector positioned on other side of the jet stream reflects the ultraviolet rays back onto the particles in the jet stream.

3 Claims, 15 Drawing Sheets



U.S. PATENT DOCUMENTS

* cited by examiner




FIG. 1A




FIG. 1B




FIG. 1C




FIG. 1D




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 3A

FIG. 3B

FIG. 3C





FIG. 3D

FIG. 3E






FIG. 3




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10

FABRICATING STRUCTURED PARTICLES THROUGH RAPID HARDENING AND TAILORED COLLECTION METHODS

STATEMENT AS TO RIGHTS TO APPLICATIONS MADE UNDER FEDERALLY SPONSORED RESEARCH AND DEVELOPMENT

The United States Government has rights in this application pursuant to Contract No. DE-AC52-07NA27344 between the United States Department of Energy and Lawrence Livermore National Security, LLC for the operation of Lawrence Livermore National Laboratory.

BACKGROUND

Field of Endeavor

The present application relates to fabricating structured particles and more particularly to fabricating structured particles through rapid hardening and tailored collection.

State of Technology

This section provides background information related to the present disclosure which is not necessarily prior art.

United States Published Patent Applications No. 2002/0054912 provides the state of technology information reproduced below.

Rapid advances in biotechnology have led to the discovery of numerous protein and peptide therapeutics, many of which have recently reached the marketplace or are currently under regulatory review by the United States Food and Drug Administration. Unlike traditional small-molecule drugs, however, proteins and peptides generally cannot be administered orally; injection or infusion is most often required. Further, because of their fragility and short in vivo half-lives, encapsulation of proteins in biodegradable polymeric devices, from which the drug can be delivered, locally or systemically, for a prolonged period of time, has been a promising and intensely studied solution to these problems. Biodegradable microspheres comprising a variety of polymers have been the most studied devices due to relatively simple fabrication and facile administration to a variety of locations in vivo through a syringe needle.

Several methodologies for microsphere fabrication have been described, including precipitation, spraying, phase separation, and emulsion techniques. The emulsion and spraying approaches have been commonly used both at the bench and industrial scales. Sphere size and size distribution are reproducible but often poorly controllable. Standard deviations equal to 25-50% of the mean diameter are not uncommon.

Control of sphere size and size distribution has several important implications for controlled-release drug delivery. For example, there typically is an ideal sphere size that provides a desired release rate and route of administration. Spheres that are "too small" exhibit poor encapsulation efficiency, may migrate from the site of injection, and may exhibit undesirably rapid release of their payload. Spheres that are "too large" may not easily pass through a syringe needle. Thus, the typically polydisperse spheres generated by conventional fabrication techniques must be filtered or sieved to isolate particles within the desired size range, and the polymer and drug composing spheres outside that range are wasted.

Uniform microspheres approximately 1-5.μm in diameter would be ideal for passive targeting of professional antigen-presenting cells (APCs) such as macrophages and dendritic cells. Similarly, microspheres 10-20.μm in diameter could be used to target the tortuous capillary bed of tumor tissues by chemoembolization. A system capable of precise microsphere fabrication could allow the optimal size for such applications to be identified and provide an efficient route to commercial manufacture and clinical implementation.

A long-sought goal for controlled-release drug delivery technologies is the ability to precisely control the release rate of encapsulated compounds, and microsphere size is a major determinant of release kinetics. Larger spheres generally release encapsulated compounds more slowly and over longer time periods, other properties (polymer molecular weight, initial porosity, drug distribution within the sphere, etc.) being equal. A constant (i.e., zero-order) release rate is often preferred, while variable drug release rates can be beneficial for many important indications. For example, intermittent high doses of antibiotics may alleviate evolution of resistance in bacteria, and discontinuous administration of vaccines often enhances the immune response.

U.S. Pat. No. 8,945,279 provides the state of technology information reproduced below.

The present invention removes the precipitation limitation of the prior art by incorporating the liquid sorbent in a thin polymer shell, forming a liquid filled bead typically 100 μm to 1 mm in diameter. This bead now is a self-contained system that can tolerate precipitation of solids during the loading phase, and that presents a uniform physical presence during the regeneration (e.g. steam stripping) phase. In this way the carrying capacity and efficiency of the incorporated liquid solvents can be increased by 25% or more.

The present invention provides a system for carbon dioxide capture from flue gas and other industrial gas sources. The present invention utilizes microcapsules with very thin polymer shells. The contents of the microcapsules can be liquids or mixtures of liquids and solids. The microcapsules are exposed to the flue gas and other industrial gas and take up carbon dioxide from the flue gas and other industrial gas and eventual precipitate solids in the capsule. In one embodiment a process is used to recover the carbon dioxide in pure form by heating the capsules to temperatures of 70 to 200 C causing the carbon dioxide to vaporize and leave the microcapsules. Other embodiments utilize chemical changes or changes in the applied pressure. The present invention has use in carbon dioxide capture from flue gas, industrial gaseous effluents, aqueous solutions, solvents, and air.

SUMMARY

Features and advantages of the disclosed apparatus, systems, and methods will become apparent from the following description. Applicant is providing this description, which includes drawings and examples of specific embodiments, to give a broad representation of the apparatus, systems, and methods. Various changes and modifications within the spirit and scope of the application will become apparent to those skilled in the art from this description and by practice of the apparatus, systems, and methods. The scope of the apparatus, systems, and methods is not intended to be limited to the particular forms disclosed and the application covers all modifications, equivalents, and alternatives falling within the spirit and scope of the apparatus, systems, and methods as defined by the claims.

3

The inventor's disclosed apparatus, systems, and methods provide the fabrication of structured particles through rapid hardening and tailored collection. The term "structured particles" as used in this application means discrete droplets. The inventor's system provides the fabrication of functional polymer-based particles by crosslinking UV-curable polymer drops in mid-air and collecting crosslinked particles in a solid container, a liquid suspension, or an air flow. The particles can contain different phases in the form or layered structures that contain one to multiple cores, or structures that are blended with dissolved or emulsified smaller domains. Particles can be spherical, oval-shaped or irregularly shaped with a size range of 1 μm -10 mm. Hardening of the particles is achieved by crosslinking the polymer precursor drop, which are generated by co-axial nozzles, with UV when the drops travel through the exposure window. Particles can also be obtained through thermal setting and solvent extraction after collection. Crosslinked particles will be gathered with different collection methods depending on their properties. The inventor's disclosed apparatus, systems, and methods have use for carbon capture, display material, chemical sensing, bio reaction, enzyme scaffold, and other applications that uses functional particles/capsules.

The apparatus, systems, and methods are susceptible to modifications and alternative forms. Specific embodiments are shown by way of example. It is to be understood that the apparatus, systems, and methods are not limited to the particular forms disclosed. The apparatus, systems, and methods cover all modifications, equivalents, and alternatives falling within the spirit and scope of the application as defined by the claims.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are incorporated into and constitute a part of the specification, illustrate specific embodiments of the apparatus, systems, and methods and, together with the general description given above, and the detailed description of the specific embodiments, serve to explain the principles of the apparatus, systems, and methods.

FIG. 1A is a simplified schematic depiction illustrating a first embodiment of the inventor's apparatus, systems, and methods for fabricating structured particles through rapid hardening and tailored collection.

FIG. 1B is a simplified schematic depiction illustrating a second embodiment of the inventor's apparatus, systems, and methods for fabricating structured particles through rapid hardening and tailored collection.

FIG. 1C is a simplified schematic depiction illustrating a third embodiment of the inventor's apparatus, systems, and methods for fabricating structured particles through rapid hardening and tailored collection.

FIG. 1D is a simplified schematic depiction illustrating a fourth embodiment of the inventor's apparatus, systems, and methods for fabricating structured particles through rapid hardening and tailored collection.

FIG. 2A is a simplified schematic depiction illustrating an embodiment of the inventor's apparatus, systems, and methods wherein the fluid jet and droplet stream are running against and at an angle to the direction of gravity.

FIG. 2B is a simplified schematic depiction illustrating another embodiment of the inventor's apparatus, systems, and methods wherein the fluid jet and droplet stream are running against and at an angle to the direction of gravity.

4

FIG. 2C is a simplified schematic depiction illustrating yet another embodiment of the inventor's apparatus, systems, and methods wherein the fluid jet and droplet stream are running against and at an angle to the direction of gravity.

FIGS. 3A-3E illustrate a number of examples of droplets that are produced by the inventor's system for fabricating structured particles through rapid hardening and tailored collection.

FIG. 4 is a simplified schematic depiction illustrating an embodiment of the inventor's apparatus, systems, and methods wherein multiple co-axial fabrication devices are ganged to provide a greater output of droplets.

FIG. 5 illustrates an embodiment of the inventor's apparatus, systems, and methods that includes a second UV curing system.

FIG. 6 illustrates an embodiment of the inventor's apparatus, systems, and methods that includes a heater for heating the material supply.

FIG. 7 illustrates an embodiment of the inventor's apparatus, systems, and methods that includes reflectors for reflecting the rays of UV Curing system back onto the droplets.

FIG. 8 illustrates an embodiment of the inventor's apparatus, systems, and methods that includes an overflow for collecting droplets that overflow from the collection system.

FIG. 9 illustrates an embodiment of the inventor's apparatus, systems, and methods that includes reflectors for reflecting the rays of UV Curing system back onto the droplets and a blocking device that prevents the UV rays from damaging components of the system.

FIG. 10 illustrates another embodiment of the inventor's apparatus, systems, and methods for fabricating structured particles.

DETAILED DESCRIPTION OF SPECIFIC EMBODIMENTS

Referring to the drawings, to the following detailed description, and to incorporated materials, detailed information about the apparatus, systems, and methods is provided including the description of specific embodiments. The detailed description serves to explain the principles of the apparatus, systems, and methods. The apparatus, systems, and methods are susceptible to modifications and alternative forms. The application is not limited to the particular forms disclosed. The application covers all modifications, equivalents, and alternatives falling within the spirit and scope of the apparatus, systems, and methods as defined by the claims.

The inventors have developed a system for fabricating structured particles through rapid hardening and tailored collection. Various embodiments of this system provide fabricating functional polymer-based particles by crosslinking UV-curable polymer drops in mid-air and collecting crosslinked particles in a solid container, a liquid suspension, or an air flow. Particles can contain different phases in the form of layered structures that contain one to multiple cores, or structures that are blended with dissolved or emulsified smaller domains. Particles can be spherical, oval-shaped or irregularly shaped with a size range of 1 μm -10 mm. Hardening of the particles is achieved by crosslinking the polymer precursor drop, which are generated by co-axial nozzles, with UV when the drops travel through the exposure window. Particles can also be obtained through thermal setting and solvent extraction after collection. Crosslinked particles are gathered with different collection methods

5

depending on their properties. Final products can be used for carbon dioxide capture, display material, chemical sensing, bio reaction, and other applications. The inventor's apparatus, systems, and methods were mainly developed for scale-up production of functional particles and capsules, which could eventually be used in applications such as carbon capture, display material, chemical sensing, bio reaction, enzyme scaffold, and other applications that uses functional particles/capsules.

Microencapsulation using vibrating technology and monodispersed particles can be made by applying vibration to a liquid stream coming out of a nozzle. In various embodiments, double-walled polymer microspheres of controllable shell thickness provide production of capsules for bio applications by producing monodispersed drops in air and collecting them in solution bath for shell formation. "Ceramic microparticles and capsules via microfluidic processing of a preceramic polymer" are produced by a microfluidic-based method for production of different capsule and particle microstructures by crosslinking emulsion drops in a liquid environment after drop generation.

This invention eliminates the need of having a carrier fluid during emulsion generation by making drops in air through injection. Drops' movement is affected by gravity, the angle of the nozzle, and the flow rate of the fluids. By using polymer precursor that can cure within seconds of UV exposure, encapsulation is completed by the time particles are collected, greatly reducing the fabrication time. Single unit production rate is 50x-1000x more than that shown in typical microfluidic-based production, and the production apparatus can be parallelized for even higher production.

In various embodiments the whole apparatus is installed inside an air-tight, sound-baffling and UV-blocking box. Cameras are set up outside the box through a viewing window for observation and characterization. Microfluidic device with co-axial nozzles are manufactured by using glass capillaries or stainless-steel tubes. The diameters of the capillaries and tubes ranged from 5 μ m to 10 mm and can be surface functionalized. Different fluids are pushed through connection pieces into the device to form a fluid jet and drops will form near the tip. Volumetric flow rates of the fluids are in the range of 1 ml/hr to 500 ml/hr for a single unit and multiplies proportionally when many units are parallelized.

A microfluidic chip can be operated as-is or with an external vibration source such as a contact speaker or piezo electric device. Negative tone photo-responsive resins to be used should be highly sensitive to the UV lamp, and contain multifunctional cross-linking monomers. Multifunctionality enables high curing rates to obtain high chemical conversions during the residence time when drops are exposed to UV. The photoinitiator compound utilized should have an absorbance peak maximum at the lamp wavelength for effective curing. Inhibitor species are to be used minimally for maintaining uncured resin stability in the syringe, tubing and device prior to exiting the device capillary. Polymer drops are cured or partially-cured before collected and post-curing can be performed for full crosslinking. During operation, an inert gas environment can be utilized for formulations composed of oxygen inhibited monomers (such as those containing acrylate species). An oxygen-free environment minimizes the induction period, providing instantaneously fast reaction speeds once the resin droplet falls within the UV exposure window. UV lamps can be stacked or used from different sides to facilitate the cross-linking of the polymer drops. In addition, polymer used in

6

drop generation can be obtained through thermal setting, solvent extraction or a combination of these.

After the particles get crosslinked, they can be collected in a container or in a liquid bath. Options of the liquid bath are solvents with a density in the range of 0.7-1.5 g/ml and surface tension in the range of 8-100 mN/m. Examples are: liquid nitrogen, isopropanol, toluene, and water-based mixtures. The fluids can be still, stirred or shaken in motion. In addition, the fabricated particles can also be collected with the aid of air flow. Air flow can come from the bottom of the container to slow down the speed of the incoming drops to reduce capsule breakage. In this case, the top rim of the collection container will extend to the device level and is composed of UV permeable material such as quartz. The air flow is distributed evenly from the bottom of the container to counteract the falling particles and soften the impact during collection. Furthermore, air flow can also be used to divert the direction of the falling particles by blowing sideways. In this case, particles will be collected in a container not directly underneath the fabrication device.

Alternatively, the drop generation apparatus can be operated at different angles and the collection bath can be placed at different locations. For example, the nozzle can face upwards at an angle. This increases the residence time of the capsules through the UV exposure window. This also decreases the capsule speed when they are collected for reduced impact that could cause bursting of the shell. Capsules can also be collected onto a slope near the apex of trajectory, transiting them into a moderate collection path. The slope can be surface treated with non-stick coating (i.e. Teflon) or covered with a layer of rinsing fluid which will be distributed from the end near the incoming particles. A UV lamp could also be placed near the slope for improved UV crosslinking.

Referring now to the drawings and in particular to FIG. 1A, a simplified schematic depiction illustrates a first embodiment of the inventor's apparatus, systems, and methods. This first embodiment is designated generally by the reference numeral **100a**. As illustrated, the embodiment **100a** includes a number of components. The components of the inventor's apparatus, systems, and methods **100a** illustrated in FIG. 1A are identified and described below.

Reference Numeral **100a**—Fabrication Device

Reference Numeral **102a**—Device

Reference Numeral **104a**—Fluid Jet

Reference Numeral **106a**—Droplets

Reference Numeral **108a**—Curing Zone

Reference Numeral **110a**—Collection System

Reference Numeral **112a**—Material Supply

Reference Numeral **118a**—Computer Controller

Reference Numeral **120a**—Vibration System

Reference Numeral **122a**—UV Curing System

The description of the fabrication device **100a** components illustrated in FIG. 1A having been completed, the operation and additional description of the inventor's first embodiment apparatus, systems, and methods will now be considered in greater detail. The jet forming device **102a** includes a nozzle that produces the jet stream **104a**. FIG. 1A shows the encapsulation apparatus with jet stream **104a** running along the direction of gravity. The material supply **112a** feeds the material into the jet forming device **102a**. The vibration system **120a** imparts vibration to the jet stream **104a** that produces the droplets **106a**. The droplets **106a** pass through the curing zone **108a** where they are cured by the UV curing system **122a**. The cured droplets **106a** are directed into the collection system **110a**. The operation of

the fabrication device **100a** is implemented and controlled by the computer controller **118a**.

Referring to FIG. 1B, a simplified schematic depiction illustrates a second embodiment of the inventor's apparatus, systems, and methods. This second embodiment is designated generally by the reference numeral **100b**. As illustrated, the embodiment **100b** includes a number of components. The components of the inventor's apparatus, systems, and methods **100b** illustrated in FIG. 1B are identified and described below.

Reference Numeral **100b**—Co-Axial Fabrication Device
 Reference Numeral **102b**—Device
 Reference Numeral **104b**—Fluid Jet
 Reference Numeral **106b**—Droplets
 Reference Numeral **108b**—Curing Zone
 Reference Numeral **110b**—Collection System
 Reference Numeral **112b**—First Material Supply
 Reference Numeral **114b**—Second Material Supply
 Reference Numeral **118b**—Computer Controller
 Reference Numeral **120b**—Vibration System
 Reference Numeral **122b**—UV Curing System

The description of the co-axial fabrication device components illustrated in FIG. 1B having been completed, the operation and additional description of the inventor's second embodiment **100b** apparatus, systems, and methods will now be considered in greater detail. The jet forming device **102b** includes a nozzle that produces the jet stream **104b**. FIG. 1B shows the encapsulation apparatus with jet stream **104b** running along the direction of gravity. The first material supply **112b** and second material supply **114b** feed the two materials into the jet forming device **102b**. The vibration system **120b** imparts vibration to the jet stream **104b** that produces the droplets **106b**. The droplets **106b** that exit the jet forming device **102b** are capsules that have an internal core of the first material **112b** and an outer shell of the second material **114b** completely surrounding the internal core of the first material **112b**. The droplets **106b** pass through the curing zone **108b** where they are cured by the UV curing system **122b**. The cured droplets **106b** are directed into the collection system **110b**. The operation of the fabrication device **100b** is implemented and controlled by the computer controller **118b**.

The present invention is further described and illustrated by a number of examples of apparatus, systems, and methods constructed in accordance with the present invention. Various changes and modifications of these examples will be apparent to those skilled in the art from the description of the examples and by practice of the invention. The scope of the invention is not intended to be limited to the particular examples disclosed and the invention covers all modifications, equivalents, and alternatives falling within the spirit and scope of the invention as defined by the claims.

Example 1—Co-Axial Fabrication Method

The whole co-axial fabrication system illustrated in FIG. 1B provides a method of fabricating functional polymer-based particles by crosslinking UV-curable polymer drops in mid-air and collecting crosslinked particles in a solid container, a liquid suspension, or an air flow. Particles contain different phases in the form or layered structures that contain one to multiple cores, or structures that are blended with dissolved or emulsified smaller domains. Particles can be spherical, oval-shaped or irregularly shaped with a size range of 1 μm -10 mm. Hardening of the particles is achieved by crosslinking the polymer precursor drop, which are generated by co-axial nozzles, with UV when the drops

travel through the exposure window. Particles can also be obtained through thermal setting and solvent extraction after collection. Crosslinked particles will be gathered with different collection methods depending on their properties. Final products can be used for carbon dioxide capture, display material, chemical sensing, bio reaction, etc.

Example 2—Co-Axial Fabrication Device

The whole co-axial fabrication device illustrated in FIG. 1B is installed inside an air-tight, sound-baffling and UV-blocking box. Cameras are set up outside the box through a viewing window for observation and characterization. Microfluidic device with co-axial nozzles are manufactured by using glass capillaries or stainless-steel tubes. The diameters of the capillaries and tubes ranged from 5 μm to 10 mm and can be surface functionalized. Different fluids are pushed through connection pieces into the device to form a fluid jet and drops will form near the tip. Volumetric flow rates of the fluids are in the range of 1 ml/hr to 500 ml/hr for a single unit and multiplies proportionally when many units are parallelized.

A microfluidic chip variation system can be operated as-is or with an external vibration source such as a contact speaker or piezo electric device. Negative tone photo-responsive resins used are highly sensitive to the UV lamp, and contain multifunctional cross-linking monomers. Multifunctionality enables high curing rates to obtain high chemical conversions during the residence time when drops are exposed to UV. The photoinitiator compound utilized must have an absorbance peak maximum at the lamp wavelength for effective curing. Inhibitor species are to be used minimally for maintaining uncured resin stability in the syringe, tubing and device prior to exiting the device capillary. Polymer drops are cured or partially-cured before collected and post-curing can be performed for full cross-linking. During operation, an inert gas environment can be utilized for formulations composed of oxygen inhibited monomers (such as those containing acrylate species). An oxygen-free environment minimizes the induction period, providing instantaneously fast reaction speeds once the resin droplet falls within the UV exposure window. UV lamps can be stacked or used from different sides to facilitate the crosslinking of the polymer drops. In addition, polymer used in drop generation can be obtained through thermal setting, solvent extraction or a combination of these.

Referring to FIG. 1C, a simplified schematic depiction illustrates a third embodiment of the inventor's apparatus, systems, and methods. This embodiment is designated generally by the reference numeral **100c**. As illustrated, the embodiment **100c** includes a number of components. The components of the inventor's apparatus, systems, and methods **100c** illustrated in FIG. 1C are identified and described below.

Reference Numeral **100c**—Co-Axial Fabrication Device
 Reference Numeral **102c**—Device
 Reference Numeral **104c**—Fluid Jet
 Reference Numeral **106c**—Droplets
 Reference Numeral **108c**—Curing Zone
 Reference Numeral **110c**—Collection System
 Reference Numeral **112c**—First Material Supply
 Reference Numeral **114c**—Second Material Supply
 Reference Numeral **116c**—Third Material Supply
 Reference Numeral **118c**—Computer Controller
 Reference Numeral **120c**—Vibration System
 Reference Numeral **122c**—UV Curing

The description of the co-axial fabrication device components illustrated in FIG. 1C having been completed, the operation and additional description of the inventor's third embodiment **100c** apparatus, systems, and methods will now be considered in greater detail. The jet forming device **102c** includes a nozzle that produces the jet stream **104c**. FIG. 1C shows the encapsulation apparatus with jet stream **104c** running along the direction of gravity. The first material supply **112c**, the second material supply **114c**, and the third material supply **116c** feed the three materials into the jet forming device **102c**. The vibration system **120c** imparts vibration to the jet stream **104c** that produces the droplets **106c**. The droplets **106c** that exit the jet forming device **102c** are capsules that have an internal core of one material, a shell of a second material, and the third material associated with the first and second materials.

Various combinations of the first, second, and third materials in the droplets **106c** can be produced by the Co-Axial Fabrication Device **100c**. For example, in one version the capsules have an internal core of the first material **112c**, a shell made of the second material **114c** that completely surrounds the internal core of the first material **112c**, and a second shell made of the third material **116c** that completely surrounds the internal core of the first material **112c** and the shell made of the second material **114c**.

The droplets **106c** pass through the curing zone **108c** where they are cured by the UV curing system **122c**. The cured droplets **106c** are directed into the collection system **110c**. The operation of the fabrication device **100b** is implemented and controlled by the computer controller **118c**.

Referring now to FIG. 1D, a simplified schematic depiction illustrates a fourth embodiment of the inventor's apparatus, systems, and methods. This fourth embodiment is designated generally by the reference numeral **100d**. As illustrated, the embodiment **100d** includes a number of components. The components of the inventor's apparatus, systems, and methods **100da** illustrated in FIG. 1D are identified and described below.

Reference Numeral **100d**—Fabrication Device
 Reference Numeral **102d**—Device
 Reference Numeral **104d**—Fluid Jet
 Reference Numeral **106d**—Droplets
 Reference Numeral **108d**—Curing/Hardening Zone
 Reference Numeral **110d**—Collection System
 Reference Numeral **112d**—Material Supply
 Reference Numeral **118d**—Computer Controller
 Reference Numeral **120d**—Vibration System
 Reference Numeral **122a**—Alternate Curing/Hardening Systems

The description of the fabrication device **100d** components illustrated in FIG. 1D having been completed, the operation and additional description of the inventor's fourth embodiment apparatus, systems, and methods will now be considered in greater detail. The jet forming device **102d** includes a nozzle that produces the jet stream **104d**. FIG. 1D shows the encapsulation apparatus with jet stream **104d** running along the direction of gravity. The material supply **112d** feeds the material into the jet forming device **102d**. The vibration system **120d** imparts vibration to the jet stream **104d** that produces the droplets **106d**. The droplets **106d** pass through the curing/hardening zone **108d** where they are cured and/or hardened by the alternate curing/hardening systems **122d**. The cured and/or hardened droplets **106d** are directed into the collection system **110d**. The operation of the fabrication device **100d** is implemented and controlled by the computer controller **118d**.

Referring to FIG. 2A, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods wherein the fluid jet and droplet stream are running against and at an angle to the direction of gravity. This embodiment is designated generally by the reference numeral **200a**. As illustrated, the embodiment **200a** includes a number of components. The components of the inventor's apparatus, systems, and methods **200a** illustrated in FIG. 2A are identified and described below.

Reference Numeral **200a**—Co-Axial Fabrication Device
 Reference Numeral **202a**—Device
 Reference Numeral **204a**—Fluid Jet
 Reference Numeral **206a**—Droplets
 Reference Numeral **208a**—Curing Zone
 Reference Numeral **210a**—Collection System
 Reference Numeral **212a**—First Material Supply
 Reference Numeral **214a**—Second Material Supply
 Reference Numeral **218a**—Computer Controller
 Reference Numeral **220a**—Vibration System
 Reference Numeral **222a**—UV Curing System
 Reference Numeral **224a**—First Pump
 Reference Numeral **226a**—Second Pump

The description of the co-axial fabrication device components illustrated in FIG. 2A having been completed, the operation and additional description of the inventor's embodiment **200a** co-axial fabrication device apparatus, systems, and methods will now be considered in greater detail. The jet forming device **202a** includes a nozzle that produces the jet stream **204a**. FIG. 2A shows the encapsulation apparatus with jet stream **204a** and the droplets **206a** running against and at an angle to the direction of gravity. The first pump **224a** and the second pump **226a** move the jet stream **204a** and the droplets **206a** against gravity.

The droplets **206a** movement is affected by gravity, the angle of the nozzle, and the flow rate of the fluids. By using polymer precursor that can cure within seconds of UV exposure, encapsulation is completed by the time particles are collected, greatly reducing the fabrication time. Single unit production rate is 50×-1000× more than that shown in typical microfluidic-based production, and the production apparatus can be parallelized for even higher production.

The first material supply **212a** and second material supply **214a** feed the two materials into the jet forming device **202a**. The vibration system **220a** imparts vibration to the jet stream **204a** that produces the droplets **206a**. The droplets **206a** that exit the jet forming device **202a** are capsules that have an internal core of the first material **212a** and an outer shell of the second material **214a** completely surrounding the internal core of the first material **212a**. The droplets **206a** pass through the curing zone **208a** where they are cured by the UV curing system **222a**. The cured droplets **206a** are directed into the collection system **210a**. The operation of the fabrication device **200a** is implemented and controlled by the computer controller **218a**.

Referring to FIG. 2B, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods wherein the fluid jet and droplet stream are running against and at an angle to the direction of gravity and there is a moveable UV curing system. This embodiment is designated generally by the reference numeral **200b**. As illustrated, the embodiment **200b** includes a number of components. The components of the inventor's apparatus, systems, and methods **200b** illustrated in FIG. 2B are identified and described below.

Reference Numeral **200b**—Co-Axial Fabrication Device
 Reference Numeral **202b**—Device
 Reference Numeral **204b**—Fluid Jet

11

Reference Numeral **206b**—Droplets
 Reference Numeral **208b**—Curing Zone
 Reference Numeral **210b**—Collection System
 Reference Numeral **212b**—First Material Supply
 Reference Numeral **214b**—Second Material Supply
 Reference Numeral **218b**—Computer Controller
 Reference Numeral **220b**—Vibration System
 Reference Numeral **222b**—UV Curing System
 Reference Numeral **224b**—First Pump
 Reference Numeral **226b**—Second Pump
 Reference Numeral **228b**—Angle

The description of the co-axial fabrication device components illustrated in FIG. 2B having been completed, the operation and additional description of the inventor's embodiment **200b** co-axial fabrication device apparatus, systems, and methods will now be considered in greater detail. The jet forming device **202b** includes a nozzle that produces the jet stream **204b**. FIG. 2B shows the encapsulation apparatus with jet stream **204b** and the droplets **206b** running against and at an angle **228b** to the direction of gravity. The first pump **224b** and the second pump **226b** move the jet stream **204b** and the droplets **206b** against gravity.

The droplets **206b** movement is affected by gravity, the angle of the nozzle, and the flow rate of the fluids. By using polymer precursor that can cure within seconds of UV exposure, encapsulation is completed by the time particles are collected, greatly reducing the fabrication time. Single unit production rate is 50×-1000× more than that shown in typical microfluidic-based production, and the production apparatus can be parallelized for even higher production.

The first material supply **212b** and second material supply **214b** feed the two materials into the jet forming device **202b**. The vibration system **220b** imparts vibration to the jet stream **204b** that produces the droplets **206b**. The droplets **206b** that exit the jet forming device **202b** are capsules that have an internal core of the first material **212b** and an outer shell of the second material **214b** completely surrounding the internal core of the first material **212b**.

The droplets **206b** pass through the curing zone **208b** where they are cured by the UV curing system **222b**. The droplet generation apparatus can be operated at different angles and the collection bath can be placed at different locations. Also, there is a moveable UV curing system. The nozzle can face upwards at an angle. This increases the residence time of the capsules through the UV exposure window. The cured droplets **206b** are directed into the collection system **210b**. The operation of the fabrication device **200b** is implemented and controlled by the computer controller **218b**.

Referring to FIG. 2C, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods wherein the fluid jet and droplet stream are running against and at an angle to the direction of gravity and there is a droplet rising system. This embodiment is designated generally by the reference numeral **200c**. As illustrated, the embodiment **200c** includes a number of components. The components of the inventor's apparatus, systems, and methods **200c** illustrated in FIG. 2C are identified and described below.

Reference Numeral **200c**—Co-Axial Fabrication Device
 Reference Numeral **202c**—Device
 Reference Numeral **204c**—Fluid Jet
 Reference Numeral **206c**—Droplets
 Reference Numeral **208c**—Curing Zone
 Reference Numeral **210c**—Collection System
 Reference Numeral **212c**—First Material Supply

12

Reference Numeral **214c**—Second Material Supply
 Reference Numeral **218c**—Computer Controller
 Reference Numeral **220c**—Vibration System
 Reference Numeral **222c**—UV Curing System
 Reference Numeral **224c**—First Pump
 Reference Numeral **226c**—Second Pump
 Reference Numeral **228c**—Rinsing Fluid Tray
 Reference Numeral **230c**—Rinsing Fluid

The description of the co-axial fabrication device components illustrated in FIG. 2C having been completed, the operation and additional description of the inventor's embodiment **200c** co-axial fabrication device apparatus, systems, and methods will now be considered in greater detail. The jet forming device **202c** includes a nozzle that produces the jet stream **204c**. FIG. 2C shows the encapsulation apparatus with jet stream **204c** and the droplets **206c** running against and at an angle to the direction of gravity. The first pump **224c** and the second pump **226c** move the jet stream **204c** and the droplets **206c** against gravity.

The droplets **206c** movement is affected by gravity, the angle of the nozzle, and the flow rate of the fluids. By using polymer precursor that can cure within seconds of UV exposure, encapsulation is completed by the time particles are collected, greatly reducing the fabrication time. Single unit production rate is 50×-1000× more than that shown in typical microfluidic-based production, and the production apparatus can be parallelized for even higher production.

The first material supply **212c** and second material supply **214c** feed the two materials into the jet forming device **202c**. The vibration system **220c** imparts vibration to the jet stream **204c** that produces the droplets **206c**. The droplets **206c** that exit the jet forming device **202c** are capsules that have an internal core of the first material **212c** and an outer shell of the second material **214c** completely surrounding the internal core of the first material **212c**.

The droplets **206c** pass through the curing zone **208c** where they are cured by the UV curing system **222c**. The droplet generation apparatus can be operated at different angles and the collection bath can be placed at different locations. Also, there is a moveable UV curing system. The nozzle can face upwards at an angle. This increases the residence time of the capsules through the UV exposure window. The cured droplets **206c** are directed into the rinsing fluid tray **228c** and rinsed by rinsing fluid **230c** before the droplets **206c** are directed into the collection system **210c**. The operation of the fabrication device **200c** is implemented and controlled by the computer controller **218c**.

Referring to FIGS. 3A-3E, a number of examples of droplets that are produced by the inventor's system for fabricating structured particles through rapid hardening and tailored collection. The examples in FIGS. 3A-3E can be produced by various combinations of the first, second, and/or third materials produced by the co-axial fabrication devices. The droplets depicted in FIGS. 3A-3E are identified by the reference numerals **300a**, **300b**, **300c**, **300d**, and **300e** respectively.

Referring to FIG. 3A, an example of a droplet **300a** produced by the inventor's system illustrated in FIG. 1A is shown. The droplet **300a** has an internal core **302a**. The droplet **300a** can have a hardened surface **304a**.

Referring to FIG. 3B, an example of a droplet **300b** produced by the inventor's system illustrated in FIG. 1B is shown. The droplet **300b** has an internal core **302b** of the first material and a shell **304b** made of the second material that completely surrounds the internal core **302b** of the first material.

13

Referring to FIG. 3C, an example of a droplet **300c** produced by the inventor's system illustrated in FIG. 1C is shown. The droplet **300c** has an internal core **302c** of the first material, a shell **304c** made of the second material that completely surrounds the internal core **302c** of the first material, and a second shell **304c** made of the third material that completely surrounds the internal core **302c** of the first material and the shell **304c** made of the second material.

Referring to FIG. 3D, an example of a droplet **300d** produced by the inventor's system for fabricating structured particles through rapid hardening and tailored collection is shown. The droplet **300d** has an internal core **302d**, a shell **304d**, and particles **306d** within the internal core **302d**.

Referring to FIG. 3E, an example of a droplet **300e** produced by the inventor's system for fabricating structured particles through rapid hardening and tailored collection is shown. The droplet **300e** has an internal core **302e**, a shell **304e**, and a matrix **306e** within the internal core **302e**.

Referring to FIG. 4, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods wherein multiple co-axial fabrication devices are ganged to provide a greater output of droplets. This embodiment is designated generally by the reference numeral **400**. As illustrated, the embodiment **400** includes a number of components. The components of the inventor's ganged multiple co-axial fabrication devices **400** illustrated in FIG. 4 are identified and described below.

Reference Numeral **400**—Multiple Co-Axial Fabrication Devices

Reference Numeral **402**—Multiple Individual Units

Reference Numeral **404**—Multiple Fluid Jets

Reference Numeral **406**—Multiple Sets of Droplets

Reference Numeral **408**—Multiple Curing Zones

Reference Numeral **410**—Multiple Collection Systems

Reference Numeral **412**—First Material Supply

Reference Numeral **414**—Second Material Supply

Reference Numeral **418**—Wi/Fi Computer Controller

Reference Numeral **420**—Vibration System

Reference Numeral **422**—UV Curing System

Reference Numeral **424**—Master Collection System

The description of the components of the inventor's ganged multiple co-axial fabrication devices **400** illustrated in FIG. 4 having been completed, the operation and additional description of the embodiment **400** will now be considered in greater detail. In many instances it is desirable to have a large output of droplets. This is accomplished by ganging multiple individual co-axial fabrication devices.

The ganged multiple co-axial fabrication devices **400** utilizes multiple individual units **402**. The multiple individual units **402** can be arranged in all conceivable formats. For example, the multiple individual units **402** can be arranged in a linear arrangement, in a circular arrangement, in a rectangular arrangement, in a multilevel arrangement, and in all other conceivable arrangements.

The multiple individual units **402** include nozzles that produce jet streams **404**. FIG. 4 shows the multiple individual units **402** with jet streams **404** running along the direction of gravity. A first material supply **412** and a second material supply **414** feed two separate materials into the jet forming devices **402**. The vibration system **420** imparts vibration to the jet streams **404** that produce the droplets **406**. The droplets **406** that exit the jet forming devices **402** are capsules that have an internal core of the first material **412** and an outer shell of the second material **414** completely surrounding the internal core of the first material **412**. The droplets **406** pass through the curing zone **408** where they are cured by the UV curing system **422**. The cured droplets

14

406 are directed into the multiple collection systems **410**. The cured droplets **406** are directed from the multiple collection systems **410** into the master collection system **424**. The operation of the ganged multiple co-axial fabrication devices **400** is implemented and controlled by the computer controller **418**.

Referring now to FIG. 5, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods that includes a second UV curing system. This embodiment is designated generally by the reference numeral **500**. As illustrated, the embodiment **500** includes a number of components. The components of the inventor's apparatus, systems, and methods **500** illustrated in FIG. 5 are identified and described below.

Reference Numeral **500**—Fabrication Device

Reference Numeral **502**—Device

Reference Numeral **504**—Fluid Jet

Reference Numeral **506**—Droplets

Reference Numeral **508**—Curing Zone

Reference Numeral **510**—Collection System

Reference Numeral **512**—Material Supply

Reference Numeral **518**—Computer Controller

Reference Numeral **520**—Vibration System

Reference Numeral **522**—UV Curing System

Reference Numeral **524**—Second UV Curing System

Reference Numeral **526**—Second Curing Zone

Reference Numeral **528**—Conveyer

The description of the fabrication device **500** components illustrated in FIG. 5 having been completed, the operation and additional description of the inventor's embodiment apparatus, systems, and methods with a second UV curing system will now be considered in greater detail. The jet forming device **502** includes a nozzle that produces the jet stream **504**. FIG. 5 shows the encapsulation apparatus with jet stream **504** running along the direction of gravity. The material supply **512** feeds the material into the jet forming device **502**. The vibration system **520** imparts vibration to the jet stream **504** that produces the droplets **506**. The droplets **506** pass through the curing zone **508** where they are cured by the UV curing system **522**. After the droplets **506** pass through the curing zone **508** they are deposited on a conveyer **528** where they pass through a second curing zone **526** where they are cured by the UV curing system **524**. In another embodiment the conveyer **528** is replaced by a dryer. The cured droplets **506** are directed into the collection system **510**. The operation of the fabrication device **500** is implemented and controlled by the computer controller **518**.

Referring now to FIG. 6, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods that includes a heater for heating the material supply. This embodiment is designated generally by the reference numeral **600**. As illustrated, the embodiment **600** includes a number of components. The components of the inventor's apparatus, systems, and methods **600** illustrated in FIG. 6 are identified and described below.

Reference Numeral **600**—Fabrication Device

Reference Numeral **602**—Device

Reference Numeral **604**—Fluid Jet

Reference Numeral **606**—Droplets

Reference Numeral **608**—Curing Zone

Reference Numeral **610**—Collection System

Reference Numeral **612**—Material Supply

Reference Numeral **614**—Heater

Reference Numeral **618**—Computer Controller

Reference Numeral **620**—Vibration System

Reference Numeral **622**—UV Curing System

15

The description of the fabrication device **600** components illustrated in FIG. **6** having been completed, the operation and additional description of the inventor's embodiment apparatus, systems, and methods with a heater for heating the material supply will now be considered in greater detail. The jet forming device **602** includes a nozzle that produces the jet stream **604**. FIG. **6** shows the encapsulation apparatus with jet stream **604** running along the direction of gravity. The material supply **612** feeds the material into the jet forming device **602**. A heater **614** heats the material from material supply **612** before it is fed into the jet forming device **602**. The vibration system **620** imparts vibration to the jet stream **604** that produces the droplets **606**. The droplets **606** pass through the curing zone **608** where they are cured by the UV curing system **622**. The cured droplets **606** are directed into the collection system **610**. The operation of the fabrication device **600** is implemented and controlled by the computer controller **618**.

Referring now to FIG. **7**, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods that includes reflectors for reflecting the rays of UV Curing system back onto the droplets. This embodiment is designated generally by the reference numeral **700**. As illustrated, the embodiment **700** includes a number of components. The components of the inventor's apparatus, systems, and methods **700** illustrated in FIG. **7** are identified and described below.

Reference Numeral **700**—Fabrication Device
 Reference Numeral **702**—Device
 Reference Numeral **704**—Fluid Jet
 Reference Numeral **706**—Droplets
 Reference Numeral **708**—Curing Zone
 Reference Numeral **710**—Collection System
 Reference Numeral **712**—Material Supply
 Reference Numeral **714**—Reflectors
 Reference Numeral **718**—Computer Controller
 Reference Numeral **720**—Vibration System
 Reference Numeral **722**—UV Curing System

The description of the fabrication device **700** components illustrated in FIG. **7** having been completed, the operation and additional description of the inventor's embodiment apparatus, systems, and methods that includes reflectors for reflecting the rays of UV Curing system back onto the droplets will now be considered in greater detail. The jet forming device **702** includes a nozzle that produces the jet stream **704**. FIG. **7** shows the encapsulation apparatus with jet stream **704** running along the direction of gravity. The material supply **712** feeds the material into the jet forming device **702**. The vibration system **720** imparts vibration to the jet stream **704** that produces the droplets **706**. The droplets **706** pass through the curing zone **708** where they are cured by the UV curing system **722**. Reflectors **714** reflecting the rays of UV Curing system **722** back onto the droplets. The cured droplets **706** are directed into the collection system **710**. The operation of the fabrication device **700** is implemented and controlled by the computer controller **718**.

Referring now to FIG. **8**, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods that includes an overflow for collecting droplets that overflow from the collection system. This embodiment is designated generally by the reference numeral **800**. As illustrated, the embodiment **800** includes a number of components. The components of the inventor's apparatus, systems, and methods **800** illustrated in FIG. **8** are identified and described below.

16

Reference Numeral **800**—Fabrication Device
 Reference Numeral **802**—Device
 Reference Numeral **804**—Fluid Jet
 Reference Numeral **806**—Droplets
 Reference Numeral **808**—Curing Zone
 Reference Numeral **810**—Collection System
 Reference Numeral **812**—Material Supply
 Reference Numeral **814**—Overflow With UV Postcure
 Reference Numeral **818**—Computer Controller
 Reference Numeral **820**—Vibration System
 Reference Numeral **822**—UV Curing System

The description of the fabrication device **800** components illustrated in FIG. **8** having been completed, the operation and additional description of the inventor's embodiment apparatus, systems, and methods that includes an overflow for collecting droplets that overflow from the collection system will now be considered in greater detail. The jet forming device **802** includes a nozzle that produces the jet stream **804**. FIG. **8** shows the encapsulation apparatus with jet stream **804** running along the direction of gravity. The material supply **812** feeds the material into the jet forming device **802**. The vibration system **820** imparts vibration to the jet stream **804** that produces the droplets **806**. The droplets **806** pass through the curing zone **808** where they are cured by the UV curing system **822**. The cured droplets **806** are directed into the collection system **810**. An overflow **814** collects droplets that overflow from the collection system. The operation of the fabrication device **800** is implemented and controlled by the computer controller **818**.

Referring now to FIG. **9**, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods that includes reflectors for reflecting the rays of UV Curing system back onto the droplets and a blocking device that prevents the UV rays from damaging components of the system. This embodiment is designated generally by the reference numeral **900**. As illustrated, the embodiment **900** includes a number of components. The components of the inventor's apparatus, systems, and methods **900** illustrated in FIG. **9** are identified and described below.

Reference Numeral **900**—Fabrication Device
 Reference Numeral **902**—Device
 Reference Numeral **904**—Fluid Jet
 Reference Numeral **906**—Droplets
 Reference Numeral **908**—Curing Zone
 Reference Numeral **910**—Collection System
 Reference Numeral **912**—Material Supply
 Reference Numeral **914**—Reflectors
 Reference Numeral **916**—Blocking System (IRIS)
 Reference Numeral **918**—Computer Controller
 Reference Numeral **920**—Vibration System
 Reference Numeral **922**—UV Curing System

The description of the fabrication device **900** components illustrated in FIG. **9** having been completed, the operation and additional description of the inventor's embodiment apparatus, systems, and methods that includes reflectors for reflecting the rays of UV Curing system back onto the droplets and a blocking device that prevents the UV rays from damaging components of the system will now be considered in greater detail. The jet forming device **902** includes a nozzle that produces the jet stream **904**. FIG. **9** shows the encapsulation apparatus with jet stream **904** running along the direction of gravity. The material supply **912** feeds the material into the jet forming device **902**. The vibration system **920** imparts vibration to the jet stream **904** that produces the droplets **906**. The droplets **906** pass through the curing zone **908** where they are cured by the UV curing system **922**. Reflectors **914** reflecting the rays of UV

Curing system **922** back onto the droplets. The blocking device **716** prevents the UV rays from damaging components of the system. The blocking device **716** can be an IRIS the is used in camera systems. The cured droplets **906** are directed into the collection system **910**. The operation of the fabrication device **900** is implemented and controlled by the computer controller **918**.

Referring now to FIG. **10**, a simplified schematic depiction illustrates an embodiment of the inventor's apparatus, systems, and methods for fabricating structured particles. This embodiment is designated generally by the reference numeral **1000**. As illustrated, the embodiment **1000** includes a number of components. The components of the inventor's apparatus, systems, and methods **1000** illustrated in FIG. **10** are identified and described below.

Reference Numeral **1000**—Structured Particles Fabrication Device

Reference Numeral **1002**—Enclosure

Reference Numeral **1004**—Device for Producing a Fluid Jet

Reference Numeral **1006**—IRIS

Reference Numeral **1008**—Jet

Reference Numeral **1010**—Droplets

Reference Numeral **1112**—UV Curing System

Reference Numeral **1114**—Enclosure Atmosphere System

Reference Numeral **1116**—Window

Reference Numeral **1118**—Camera

Reference Numeral **1120**—Reflector

Reference Numeral **1122**—Heated Material Supply

Reference Numeral **1124**—Collection System

Reference Numeral **1126**—Overflow System

Reference Numeral **1128**—Computer/Controller

Reference Numeral **1130**—Vibration System

The description of the inventor's apparatus, systems, and methods for fabricating structured particles **1000** components illustrated in FIG. **10** having been completed, the operation and additional description of the inventor's embodiment apparatus, systems, and methods will now be considered in greater detail. An enclosure **1002** houses the apparatus, systems, and methods for fabricating structured particles **1000**. An Enclosure Atmosphere System **1114** maintains the atmosphere inside the enclosure **1002**. The Device for Producing a Fluid Jet **1004** provides a nozzle that produces the jet stream **1008**. FIG. **10** shows the jet stream **1008** running along the direction of gravity. The heated material supply **1122** feeds the material into the jet forming device **1004**. A heater heats the material in Heated Material Supply **1122** before it is fed into the jet forming device **1004**. The vibration system **1130** imparts vibration to the jet stream **1008** that produces the droplets **1010**. The droplets **1010** pass through the curing zone where they are cured by the UV Curing System **1112**. A Reflector **1120** is positioned opposite the UV Curing System **1112** to reflect UV rays back onto the Droplets **1010**. The IRIS **1006** prevents the UV rays from escaping the Enclosure **1002** and causing damage. The Fast Camera **1118** and Window **1116** provide light for photographing the formation of the Droplets **1010**. The cured Droplets **1010** are directed into the Collection System **1024**. An Overflow System **1126** allows the apparatus, systems, and methods for fabricating structured particles **1000** to continue operation even when the Collection System **1024** becomes full. The operation of the fabrication device **1000** is implemented and controlled by the Computer/Controller **1128**.

The inventor's apparatus, systems, and methods for fabricating structured particles is further described and illus-

trated with reference to the drawing figures and as described below. Various changes and modifications of the examples will be apparent to those skilled in the art from the description of the examples and by practice of the invention. The scope of the invention is not intended to be limited to the particular examples disclosed and the invention covers all modifications, equivalents, and alternatives falling within the spirit and scope of the invention as defined by the claims.

The inventor's apparatus, systems, and methods for fabricating structured particles whole apparatus is installed inside an air-tight, sound-baffling and UV-blocking box. Cameras are set up outside the box through a viewing window for observation and characterization. Microfluidic device with co-axial nozzles are manufactured by using glass capillaries or stainless steel tubes. The diameters of the capillaries and tubes ranged from 5 μm to 10 mm and can be surface functionalized. Different fluids are pushed through connection pieces into the device to form a fluid jet and drops will form near the tip. Volumetric flow rates of the fluids are in the range of 1 ml/hr to 500 ml/hr for a single unit and multiplies proportionally when many units are parallelized.

The microfluidic chip can be operated as-is or with an external vibration source such as a contact speaker or piezo electric device). Negative tone photo-responsive resins to be used in this invention must be highly sensitive to the UV lamp, and contain multifunctional cross-linking monomers. Multifunctionality enables high curing rates to obtain high chemical conversions during the residence time when drops are exposed to UV. The photoinitiator compound utilized must have an absorbance peak maximum at the lamp wavelength for effective curing. Inhibitor species are to be used minimally for maintaining uncured resin stability in the syringe, tubing and device prior to exiting the device capillary. Polymer drops are cured or partially-cured before collected and post-curing can be performed for full cross-linking. During operation, an inert gas environment can be utilized for formulations composed of oxygen inhibited monomers (such as those containing acrylate species). An oxygen-free environment minimizes the induction period, providing instantaneously fast reaction speeds once the resin droplet falls within the UV exposure window. UV lamps can be stacked or used from different sides to facilitate the crosslinking of the polymer drops. In addition, polymer used in drop generation can be obtained through thermal setting, solvent extraction or a combination of these.

After the particles get crosslinked, they can be collected in a container or in a liquid bath. Options of the liquid bath are solvents with a density in the range of 0.7-1.5 g/ml and surface tension in the range of 8-100 mN/m. Examples are: liquid nitrogen, isopropanol, toluene, and water-based mixtures. The fluids can be still, stirred or shaken in motion. In addition, the fabricated particles can also be collected with the aid of air flow. Air flow can come from the bottom of the container to slow down the speed of the incoming drops to reduce capsule breakage. In this case, the top rim of the collection container will extend to the device level and is composed of UV permeable material such as quartz. The air flow is distributed evenly from the bottom of the container to counteract the falling particles and soften the impact during collection. Furthermore, air flow can also be used to divert the direction of the falling particles by blowing sideways. In this case, particles will be collected in a container not directly underneath the fabrication device. Alternatively, the drop generation apparatus can be operated at different angles and the collection bath can be placed at different locations. For example, the nozzle can face

upwards at an angle. This increases the residence time of the capsules through the UV exposure window. This also decreases the capsule speed when they are collected for reduced impact that could cause bursting of the shell. Capsules can also be collected onto a slope near the apex of trajectory, transiting them into a moderate collection path. The slope can be surface treated with non-stick coating (i.e. Teflon) or covered with a layer of rinsing fluid which will be distributed from the end near the incoming particles. A UV lamp could also be placed near the slope for improved UV crosslinking.

Although the description above contains many details and specifics, these should not be construed as limiting the scope of the application but as merely providing illustrations of some of the presently preferred embodiments of the apparatus, systems, and methods. Other implementations, enhancements and variations can be made based on what is described and illustrated in this patent document. The features of the embodiments described herein may be combined in all possible combinations of methods, apparatus, modules, systems, and computer program products. Certain features that are described in this patent document in the context of separate embodiments can also be implemented in combination in a single embodiment. Conversely, various features that are described in the context of a single embodiment can also be implemented in multiple embodiments separately or in any suitable subcombination. Moreover, although features may be described above as acting in certain combinations and even initially claimed as such, one or more features from a claimed combination can in some cases be excised from the combination, and the claimed combination may be directed to a subcombination or variation of a subcombination. Similarly, while operations are depicted in the drawings in a particular order, this should not be understood as requiring that such operations be performed in the particular order shown or in sequential order, or that all illustrated operations be performed, to achieve desirable results. Moreover, the separation of various system components in the embodiments described above should not be understood as requiring such separation in all embodiments.

Therefore, it will be appreciated that the scope of the present application fully encompasses other embodiments which may become obvious to those skilled in the art. In the claims, reference to an element in the singular is not intended to mean "one and only one" unless explicitly so stated, but rather "one or more." All structural and functional equivalents to the elements of the above-described preferred embodiment that are known to those of ordinary skill in the art are expressly incorporated herein by reference and are intended to be encompassed by the present claims. Moreover, it is not necessary for a device to address each and every problem sought to be solved by the present apparatus, systems, and methods, for it to be encompassed by the present claims. Furthermore, no element or component in the present disclosure is intended to be dedicated to the public regardless of whether the element or component is explicitly recited in the claims. No claim element herein is to be construed under the provisions of 35 U.S.C. 112, sixth paragraph, unless the element is expressly recited using the phrase "means for."

While the apparatus, systems, and methods may be susceptible to various modifications and alternative forms, specific embodiments have been shown by way of example in the drawings and have been described in detail herein. However, it should be understood that the application is not intended to be limited to the particular forms disclosed.

Rather, the application is to cover all modifications, equivalents, and alternatives falling within the spirit and scope of the application as defined by the following appended claims.

The invention claimed is:

1. An apparatus for fabricating structured particles in mid-air using gravity that has a direction of gravity, comprising:

a fluid jet forming unit that produces a fluid jet stream wherein said fluid jet forming unit is positioned to direct said fluid jet stream against said direction of gravity;

a material supply connected to said fluid jet forming unit that feeds material into said fluid jet forming unit, wherein said fluid jet stream is made of said material;

a vibration system connected to said fluid jet forming unit and positioned proximate said fluid jet forming unit that imparts vibration to said fluid jet stream and produces a particle fluid jet stream having discrete droplets made of said material wherein said particle fluid jet stream is positioned to run against the direction of gravity;

a curing system positioned in the mid-air proximate said particle fluid jet stream that cures said discrete droplets and produces cured droplets; and

a collection system located above said curing system operably positioned to receive said cured droplets from said curing system that receives said cured droplets thereby providing the structured particles.

2. The apparatus for fabricating structured particles of claim 1 further comprising a rinsing fluid tray located above said particle fluid jet stream that runs against the direction of gravity and operably positioned to receive said cured droplets wherein said cured droplets are rinsed and directed to said collection system.

3. An apparatus for fabricating structured particles in mid-air using gravity that has a direction of gravity, comprising:

an enclosure;

an enclosure atmosphere system that maintains an atmosphere inside said enclosure;

a fluid jet forming unit that produces a fluid jet stream in said atmosphere wherein said fluid jet stream runs along the direction of gravity;

a material supply that includes a heater that produces heated material wherein said material supply is connected to said fluid jet forming unit and feeds said heated material into said fluid jet forming unit;

wherein said fluid jet stream is made of said heated material;

a vibration system positioned proximate said fluid jet stream that imparts vibration to said fluid jet stream and produces a particle fluid jet stream having discrete droplets wherein said particle fluid jet stream runs along the direction of gravity;

an iris positioned below said particle fluid jet stream wherein said particle fluid jet stream passes through said iris;

wherein said particle fluid jet stream has one side and another side opposite side said one side;

a fast camera positioned on said one side of said particle fluid jet stream below said iris to photograph said particle fluid jet stream and said discrete droplets;

a window on said other side of said particle fluid jet stream that provides light for photographing said particle fluid jet stream;

21

a curing system in mid-air positioned proximate said
particle fluid jet stream that produces ultraviolet rays
that are directed onto said particle fluid jet stream from
said one side;
at least one reflector positioned on said other side of said 5
particle fluid jet stream that reflects said ultraviolet rays
back onto said particle fluid jet stream;
a collection system that receives said discrete droplets
thereby providing the structured particles; and
an overflow system connected to said collection system. 10

* * * * *

22