



US011788207B2

(12) **United States Patent**
Bidhar

(10) **Patent No.:** **US 11,788,207 B2**
(45) **Date of Patent:** **Oct. 17, 2023**

(54) **METHODS AND SYSTEMS FOR ELECTROSPINNING USING LOW POWER VOLTAGE CONVERTER**

5/003; D01D 5/0038; D01D 5/0046; D01D 5/0061; D01D 5/0069; D01D 5/0076; D01D 5/0092; D01D 7/00; D01D 13/00; D01D 13/02

(71) Applicant: **Fermi Research Alliance, LLC**,
Batavia, IL (US)

USPC 264/211.12, 464, 465, 466, 484; 425/174.8 E, 377, 382.2

(72) Inventor: **Sujit Bidhar**, Carol Stream, IL (US)

See application file for complete search history.

(73) Assignee: **Fermi Research Alliance, LLC**,
Batavia, IL (US)

(56) **References Cited**

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

U.S. PATENT DOCUMENTS

5,295,039 A 3/1994 Nakajima et al.
6,753,454 B1 6/2004 Smith et al.
(Continued)

(21) Appl. No.: **17/502,611**

FOREIGN PATENT DOCUMENTS

(22) Filed: **Oct. 15, 2021**

CN 102828260 A * 12/2012 D01D 1/06
CN 105970310 A * 9/2016 D01D 5/0076
JP 2015081391 A * 4/2015 D01D 5/04

(65) **Prior Publication Data**

US 2022/0033994 A1 Feb. 3, 2022

Related U.S. Application Data

OTHER PUBLICATIONS

(63) Continuation of application No. 16/266,569, filed on Feb. 4, 2019, now Pat. No. 11,174,570.
(Continued)

Translation of CN 102828260 A (published on Dec. 19, 2012).*
(Continued)

(51) **Int. Cl.**
D01D 1/02 (2006.01)
D01D 1/06 (2006.01)
(Continued)

Primary Examiner — Leo B Tentoni
(74) *Attorney, Agent, or Firm* — LOZA & LOZA, LLP;
Kevin L. Soules


(52) **U.S. Cl.**
CPC **D01D 5/0084** (2013.01); **D01D 5/0038** (2013.01); **D01D 5/0061** (2013.01); **D01D 5/0069** (2013.01); **D01D 5/0076** (2013.01); **D01D 5/0092** (2013.01); **D01F 1/09** (2013.01); **D01F 6/94** (2013.01); **D01D 10/00** (2013.01)

(57) **ABSTRACT**

An electrospinning system, method, and apparatus comprises a dual polarity high voltage power supply with much less power out for safe operation, a solution dispensing assembly held at high positive potential by the dual polarity power supply, a Corona discharge assembly held at high negative potential by the dual polarity power supply, and a drum collector held at ground potential wherein a solution is drawn from the solution dispensing assembly to the drum collector thereby forming a fiber mat.

(58) **Field of Classification Search**
CPC .. D01D 1/02; D01D 1/06; D01D 4/02; D01D 4/06; D01D 5/0007; D01D 5/0015; D01D

20 Claims, 13 Drawing Sheets



Related U.S. Application Data

(60) Provisional application No. 62/626,215, filed on Feb. 5, 2018.

(51) **Int. Cl.**

D01D 4/02 (2006.01)
D01D 4/06 (2006.01)
D01D 7/00 (2006.01)
D01D 13/00 (2006.01)
D01D 13/02 (2006.01)
D01D 5/00 (2006.01)
D01F 6/94 (2006.01)
D01F 1/09 (2006.01)
D01D 10/00 (2006.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,264,762 B2 9/2007 Ko et al.
 8,518,320 B2 8/2013 Steckl et al.
 2002/0084178 A1 7/2002 Dubson et al.

2004/0156904 A1* 8/2004 Saltman A61K 9/5192
 514/44 R

2006/0226580 A1 10/2006 Xia et al.
 2006/0228435 A1 10/2006 Andrady et al.
 2006/0264140 A1 11/2006 Andrady et al.
 2006/0290031 A1 12/2006 Jirsak et al.
 2009/0127748 A1 5/2009 Takahashi
 2010/0233115 A1 9/2010 Patel et al.
 2014/0079759 A1 3/2014 Patel et al.
 2014/0353882 A1 12/2014 Joo et al.
 2016/0047062 A1 2/2016 Greenawalt
 2016/0047063 A1 2/2016 Khandaker et al.
 2018/0223451 A1* 8/2018 King D01D 5/0092

OTHER PUBLICATIONS

Translation of CN 105970310 A (published on Sep. 28, 2016).*
 Translation of JP 2015081391 A (published on Apr. 27, 2015).*
 Shi-Cong Xu et al., "A battery-operated portable handheld electrospinning apparatus", *Nanoscale*, 2015, 7, 12351.
 Pierre-Alexis Mouthuy et al., "Performances of a portable electrospinning apparatus", *Biotechnol Lett* (2015)37:1107-1116.

* cited by examiner




FIG. 1






FIG. 2






FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 6D




FIG. 6E




FIG. 7

1

METHODS AND SYSTEMS FOR ELECTROSPINNING USING LOW POWER VOLTAGE CONVERTER

CROSS REFERENCE TO RELATED PATENT APPLICATIONS

The present application is a continuation of U.S. Pat. No. 11,174,570 (U.S. patent application Ser. No. 16/266,569) a titled "METHODS AND SYSTEMS FOR ELECTROSPINNING USING LOW POWER VOLTAGE CONVERTER" filed Feb. 4, 2019. U.S. patent application Ser. No. 16/266,569 is herein incorporated by reference in its entirety.

STATEMENT OF GOVERNMENT RIGHTS

The invention described in this patent application was made with Government support under the Fermi Research Alliance, LLC, Contract Number DE-AC02-07CH11359 awarded by the U.S. Department of Energy. The Government has certain rights in the invention.

TECHNICAL FIELD

Embodiments are generally related to electrospinning. Embodiments are further related to methods and systems for manufacturing nanofiber. Embodiments are additionally related to methods and systems for producing a variety of ceramic nanofibers using very low power output and low voltage DC input using DC to DC voltage converters with dual polarity and a high voltage DC supply.

BACKGROUND

Electrospinning is a method used to produce polymeric nanofiber. Electrospinning methods typically require application of high voltage to a drop of liquid, causing the liquid to become charged. The charged liquid droplet is then stretched toward a collector. The elongated droplet dries as it travels to the collector. The drying fiber is subject to a whipping process that increases the path of travel, resulting in the formation of very thin fibers.

Conventional electrospinning requires sophisticated and expensive power supply units which are bulky, operate at high input voltage, and have high power output (e.g. running into the hundreds of watts). Such systems pose electrical hazards. In cases where it is desirable to have both positive and negative high voltage output, two such power supplies are required, effectively doubling the problems associated with the system complexity, bulkiness, and safety.

Accordingly, there is a need in the art for improved methods, systems, and apparatuses for electrospinning as disclosed herein.

SUMMARY

The following summary is provided to facilitate an understanding of some of the innovative features unique to the embodiments disclosed and is not intended to be a full description. A full appreciation of the various aspects of the embodiments can be gained by taking the entire specification, claims, drawings, and abstract as a whole.

It is, therefore, one aspect of the disclosed embodiments to provide a method and system for electrospinning.

It is another aspect of the disclosed embodiments to provide a method and system for producing a variety of nanofibers.

2

It is another aspect of the disclosed embodiments to provide methods, systems, and apparatuses for producing a variety of ceramic nanofibers using very low power output and low voltage DC input using DC to DC voltage converters with dual polarity and a high voltage DC supply.

The aforementioned aspects and other objectives and advantages can now be achieved as described herein. The embodiments disclosed herein comprise an electrospinning system, method, and apparatus with a dual polarity power supply, a solution dispensing assembly held at high positive potential by the dual polarity power supply, a Corona discharge assembly held at high negative potential by the dual polarity power supply, and a drum collector held at ground potential wherein a solution is drawn from the solution dispensing assembly to the drum collector thereby forming a fiber mat.

In an embodiment, the solution dispensing assembly comprises at least one dispensing needle, a manifold attached to a syringe, the manifold connecting the syringe to the at least one dispensing needle, and a syringe pump for pumping the solution from the syringe through the manifold to the dispensing needle. In another embodiment, the solution dispensing assembly comprises a solution tank holding the solution, a rotating spindle, at least one solid needle on the rotating spindle, and a motor for rotating the spindle.

In an embodiment, the corona discharge assembly comprises a plate with a knife edge connected to the dual polarity power supply. In another embodiment, the corona discharge assembly comprises an array of micro-tipped needles connected to the dual polarity power supply.

In another embodiment an electrospinning system or apparatus comprises a power supply, a solution dispensing assembly held at positive potential by the power supply, a Corona discharge assembly held at negative potential by the power supply, and a collector wherein a solution is drawn from the solution dispensing assembly to the collector forming a fiber mat thereon. The power supply can comprise a dual polarity power supply.

In an embodiment, the solution dispensing assembly comprises at least one dispensing needle, a manifold attached to a syringe, the manifold connecting the syringe to the at least one dispensing needle, and a syringe pump for pumping the solution to the dispensing needle. In an embodiment the solution dispensing assembly comprises a solution tank containing the solution, a rotating spindle, at least one solid needle on the rotating spindle, and a motor for rotating the spindle.

In an embodiment, the Corona discharge assembly comprises a plate with a knife edge. In an embodiment the Corona discharge assembly comprises an array of at least one micro-tipped needles.

In an embodiment, the collector comprises a drum collector. A ground can be connected to the drum collector. In another embodiment the collector comprises a conveyor belt assembly. In an embodiment the conveyor belt assembly further comprises a ground plate, the ground plate being held at ground potential, and a conveyor belt wrapping around the ground plate.

Various additional embodiments and descriptions are provided herein.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying figures, in which like reference numerals refer to identical or functionally-similar elements throughout the separate views and which are incorporated in and form a part of the specification, further illustrate the

embodiments and, together with the detailed description, serve to explain the embodiments disclosed herein.

FIG. 1 depicts a block diagram of an electrospinning system, in accordance with the disclosed embodiments;

FIG. 2 depicts a photograph of a nanofiber mat that can be produced according to the methods and systems disclosed herein;

FIG. 3A depicts a dual power supply, in accordance with the disclosed embodiments;

FIG. 3B depicts a dual power supply, in accordance with the disclosed embodiments;

FIG. 4 depicts a block diagram of an electrospinning system, in accordance with the disclosed embodiments;

FIG. 5A depicts a block diagram of an electrospinning system, in accordance with the disclosed embodiments;

FIG. 5B depicts a block diagram of another aspect of an electrospinning system, in accordance with the disclosed embodiments;

FIG. 5C depicts a bottom view of a conveyor belt assembly associated with an electrospinning system, in accordance with the disclosed embodiments;

FIG. 6A depicts a block diagram of an electrospinning system, in accordance with the disclosed embodiments;

FIG. 6B depicts an elevation view of an electrospinning component, in accordance with the disclosed embodiments;

FIG. 6C depicts a cutaway view of a dispenser associated with an electrospinning system, in accordance with the disclosed embodiments;

FIG. 6D depicts a cutaway view of a dispenser and a rotating cylinder associated with an electrospinning system, in accordance with the disclosed embodiments;

FIG. 6E depicts a view of a dispenser associated with an electrospinning system, in accordance with the disclosed embodiments; and

FIG. 7 depicts steps associated with a method for producing a nanofiber mat, in accordance with the disclosed embodiments.

DETAILED DESCRIPTION

The particular values and configurations discussed in the following non-limiting examples can be varied, and are cited merely to illustrate one or more embodiments and are not intended to limit the scope thereof.

Example embodiments will now be described more fully hereinafter, with reference to the accompanying drawings, in which illustrative embodiments are shown. The embodiments disclosed herein can be embodied in many different forms and should not be construed as limited to the embodiments set forth herein; rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the embodiments to those skilled in the art. Like numbers refer to like elements throughout.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a”, “an”, and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprises” and/or “comprising,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

Throughout the specification and claims, terms may have nuanced meanings suggested or implied in context beyond

an explicitly stated meaning. Likewise, the phrase “in one embodiment” as used herein does not necessarily refer to the same embodiment and the phrase “in another embodiment” as used herein does not necessarily refer to a different embodiment. It is intended, for example, that claimed subject matter include combinations of example embodiments in whole or in part.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

It is contemplated that any embodiment discussed in this specification can be implemented with respect to any method, kit, reagent, or composition of the invention, and vice versa. Furthermore, compositions of the invention can be used to achieve methods of the invention.

It will be understood that particular embodiments described herein are shown by way of illustration and not as limitations of the invention. The principal features of this invention can be employed in various embodiments without departing from the scope of the invention. Those skilled in the art will recognize, or be able to ascertain using no more than routine experimentation, numerous equivalents to the specific procedures described herein. Such equivalents are considered to be within the scope of this invention and are covered by the claims.

The use of the word “a” or “an” when used in conjunction with the term “comprising” in the claims and/or the specification may mean “one,” but it is also consistent with the meaning of “one or more,” “at least one,” and “one or more than one.” The use of the term “or” in the claims is used to mean “and/or” unless explicitly indicated to refer to alternatives only or the alternatives are mutually exclusive, although the disclosure supports a definition that refers to only alternatives and “and/or.” Throughout this application, the term “about” is used to indicate that a value includes the inherent variation of error for the device, the method being employed to determine the value, or the variation that exists among the study subjects.

As used in this specification and claim(s), the words “comprising” (and any form of comprising, such as “comprise” and “comprises”), “having” (and any form of having, such as “have” and “has”), “including” (and any form of including, such as “includes” and “include”) or “containing” (and any form of containing, such as “contains” and “contain”) are inclusive or open-ended and do not exclude additional, unrecited elements or method steps.

The term “or combinations thereof” as used herein refers to all permutations and combinations of the listed items preceding the term. For example, “A, B, C, or combinations thereof” is intended to include at least one of: A, B, C, AB, AC, BC, or ABC, and if order is important in a particular context, also BA, CA, CB, CBA, BCA, ACB, BAC, or CAB. Continuing with this example, expressly included are combinations that contain repeats of one or more item or term, such as BB, AAA, AB, BBC, AAABCCCC, CBBAAA, CABABB, and so forth. The skilled artisan will understand that typically there is no limit on the number of items or terms in any combination, unless otherwise apparent from the context.

All of the compositions and/or methods disclosed and claimed herein can be made and executed without undue

experimentation in light of the present disclosure. While the compositions and methods of this invention have been described in terms of preferred embodiments, it will be apparent to those of skill in the art that variations may be applied to the compositions and/or methods and in the steps or in the sequence of steps of the method described herein without departing from the concept, spirit and scope of the invention. All such similar substitutes and modifications apparent to those skilled in the art are deemed to be within the spirit, scope and concept of the invention as defined by the appended claims.

The embodiments disclosed herein are drawn to methods, systems, and apparatuses for electrospinning. Electrospinning can be understood as a process for producing polymeric fiber. In some embodiments, this can include producing nanofiber mats. Generally, electrospinning operates by applying a high voltage to a specially prepared liquid that is formed into droplets at a dispensing point, such as a needle. The body of the drop is charged by the high voltage. Electrostatic repulsion creates a stream of liquid, that is ejected from the dispensing point, commonly referred to as a "Taylor Cone." The liquid stream dries as it travels toward a grounded collector. The drying liquid stream can be elongated by a whipping process. The dried and whipped fiber collects on the collector in a mat of generally, thin and uniform fiber.

The embodiments disclosed herein describe compact nanofiber (i.e., electrospinning) production systems with the ability to produce a variety of ceramic nanofibers or polymeric materials. The nanofiber production systems can have very low power output and low voltage DC input. This is made possible by using a DC to DC voltage converter with a dual polarity high voltage DC supply, as disclosed herein.

FIG. 1 illustrates an embodiment of an electrospinning system 100 employing a dual polarity source 115, for mass production of a nanofiber mat comprising Zirconia, or other such ceramic material (e.g. alumina, Tungsten oxide, Titania, etc.), using one or more dispensing needles in a needle array 120.

The system 100 takes advantage of Corona discharge. Corona discharge creates oppositely charged ions to neutralize charge accumulation on the nanofiber mat thereby enabling the creation of a thick nanofiber mat.

In FIG. 1, a rotating collector 105 (e.g. a drum collector) is held at ground potential via ground 170. A Corona discharge assembly 175 can include a plate 110, having a knife edge 111, connected to a DC voltage source 115 that drives the Corona discharge. Nanofibers are ejected from one or more needles in the needle array 120 as shown. It should be appreciated that in FIG. 1, four needles in needle array 120 are shown but in other embodiments the number of needles can vary according to the scale of the system 100 and size of the desired nanofiber mat 125. For example, the number of needles can be adjusted to accommodate production of a larger/smaller or wider/narrower nanofiber mat. Arrangement of the needles in needle array 120 need not be linear. For example, in other embodiments, the needles in needle array 120 can be staggered or otherwise configured in any number of ways along needle manifold 155.

The system 100 can include a dual polarity power supply 115 connected to a solution dispensing assembly 130. The solution dispensing system 130 includes an actuator 140 that is connected to a syringe pump 145. The actuator 140 is fixed to a plunger 150 that is connected to a needle manifold 155. The syringe pump 145 controls the actuator 140, which pushes liquid 160 to the needle array 120 through the needle manifold 155.

The liquid 160 can comprise positively charged ions of a desired material. In certain embodiments the liquid 160 can include possible precursor solutions including Alumina→Aluminum 2,4-pentadionate+Aceton, Zirconia→Zirconium Carbonate+Acetic Acid, WO_3 →Ammonium metatungstate+D.I. Water, and TiO_2 →Titanium Isopropoxide. These solutions can be added with polymeric solution containing approximately 5-8 wt % of polyvinylpyrrolidone in Acetone or Ethanol.

The needle manifold 155 can be configured to include one or more needle ports 121 that connect the one or more needles in the needle array 120 to the needle manifold 155. In certain embodiments, the needle array 120, illustrated in FIG. 1, can comprise blunt needles with an internal diameter on the order of a few hundred microns.

In the embodiment illustrated in FIG. 1, the needle manifold 155 can comprise a manifold and has been designed to hold the needle array 120 at high +Ve potential. The needle manifold 155 can be 3-D printed, or can be manufactured according to other known techniques. The knife edge 111 on plate 110 is similarly maintained at a high -Ve potential to generate -Ve ions. In combination, this assembly increases the production rate of the electrospinning system 100.

A certain distance, for example, 1-5 centimeters can be maintained between the needles 120 to avoid squeezing the nanofiber cone volume that emanates from the needles 120 during use. Nanofiber constituted liquid emerging from each needle in the needle array 120 travels to the ground plate 110 in a spiral action which results in a cone like formation. Since each of the nanofibers emanating from the needle array 120 are of the same charge, they increasingly repel each other according to their relative proximity, thereby squeezing the cone of travel. Eventually this squeezing action can become sufficiently prevalent that it will lead to non-uniform deposition of nanofibers on the drum collector. Thus, in the embodiments disclosed herein, an exemplary distance between needles in the needle array 120 should be maintained to prevent this effect. In certain embodiments this distance can be at least 1 inch. This distance is sufficient to avoid squeezing of the spinning area from individual needles, due to charge repulsion, while allowing for some overlap to produce uniformity in the axial direction of the rotating collector 105.

Appropriate distance and voltage can also be maintained between the rotating collector 105 and the knife edge 111 to prevent the breakdown of air which could result in a spark instead of ionization. Although the rotating collector 105 and knife edge 111 are illustrated in FIG. 1, in other embodiments, a set of micro-tipped (e.g., approximately 10 micron tip diameter) tungsten/metallic needles can also be used to produce corona discharge, as further detailed in the embodiments presented herein.

Thus, in the embodiment illustrated in FIG. 1, the power supply 115 provides a positive DC voltage to the needle array 120 and a negative DC voltage to the knife edge 111 positioned near the rotating drum collector 105, which is kept at ground potential. The potential difference between the needle array 120 and the drum/knife edge 111 provides the attractive force that results in the thin liquid jet depositing material 125 on the rotating drum 105. The drum 105 is rotated with a motor 165 connected to a drive shaft 180, so that a mat of surrounding fiber 125 is deposited on the drum 105.

A photograph of the collected fiber 205 is illustrated in FIG. 2. The photograph in FIG. 2 illustrates a thick Zirconia

nanofiber mat **205**. It should be appreciated that in other embodiments, other materials can be used to produce mats of such materials.

In the embodiments disclosed herein, a critical aspect is the power supply **115**, which can use a low voltage DC input and inexpensive DC to DC voltage converters with a dual polarity high voltage DC supply. A major advantage realized by this arrangement is that the power supply **115** can be, for example, limited to 4 watts of output power while maintaining a 0 to 40 kV DC and 0 to -20 kV DC output in dual polarity mode, simultaneously from a 9V/12V DC battery or a 12 V DC adapter. Thus, the power supply **115** can be characterized as having a nominal input voltage of 12 V DC, a voltage range of approximately 9 V-32 V DC, an output voltage of approximately 0 to +40 kV DC and 0 to -20 kV DC, indefinite output short-circuit protection, and ripple of 0.02.

FIGS. **3A** and **3B** illustrate an exemplary embodiment of the dual power supply **115**. Two power units (one +40 kV and one -20 kV) can be assembled inside a housing **305** as illustrated in FIG. **3A**. It should be understood that housing **305** can comprise a metal box, or other such housing. Each power unit has an individual potentiometer to vary input voltage, which, in turn, can be used to vary the high voltage output from approximately 0-40 kV DC. A potentiometer **320** can be provided for the first power supply and a second potentiometer **321** can be provided for the other power supply in the housing **305**. The housing **305** can further include a display **325**. The housing can provide a voltage sensor port **310** and current sensor port **315** associated with one power supply, and a second voltage sensor port **311** and current sensor port **316** associated with the other power supply.

FIG. **3B** shows inside the assembled power supply **115**. The power supply **115** includes two high voltage converters (one positive high voltage converter **330** and one negative high voltage converter **331**) connected with a connector junction **335**. The positive high voltage power converter **330** is connected to a high voltage DC output **355**. The negative high voltage power converter **331** is connected to a high voltage DC output **356**. The positive voltage converter **330** has a junction box **340** for connecting to the potentiometer, voltage and optional voltage/current display. Likewise, the negative voltage converter **331** has a junction box **341** for connecting to the potentiometer, voltage and the optional voltage/current display. The output voltage/current sensing ports can be connected to the digital display unit **325** for easy readability.

As illustrated in FIG. **3B**, the voltage supply assemblies are simple and connections can be made easily, without the need for complicated printed circuit boards, although in certain embodiments PCBs can alternatively be used. The grounding wire **345** can be connected to the box **305** for safety purposes. Likewise, spark protection lug **350** and spark protection lug **351** can be provided. It is important to select an appropriate length for the spark protection lugs **350** and **351**, and to maintain safe distances between the high voltage cable and exposed wire to the nearby ground/metal surface.

It should be appreciated that the dual polarity power supply assembly **115** illustrated in FIGS. **3A** and **3B** is useful for producing a thicker nanofiber mat. The embodiments disclosed herein can use the dual polarity high voltage assembly **115** such that one polarity drives the nanofiber production while the opposite polarity is used for the negatively charged ions, which results in the Corona discharge through the specially arranged needle array. Dual polarity

also results in an effective potential drop of up to 60 KV DC. Such high potential is necessary for mass producing larger nanofiber mats using a needleless spinneret system as further detailed herein.

FIG. **4** illustrates another embodiment of a dual source electrospinning system **400**. Thick fiber mat production can be achieved using the system **400**, illustrated in FIG. **4**. The system **400** comprises two sets of syringe needles held at opposite polarities. In FIG. **4**, positive syringe needles in needle array **405** and negative syringe needles in needle array **406** are shown.

As in FIG. **1**, needle array **405** and needle array **406** are supplied liquid **160** via manifolds which are connected to the needle arrays. In this embodiment, the first manifold **410** is connected to syringe **415** and the second manifold **411** is connected to syringe **416**. Liquid **160** in the syringes **415** and **416** is pumped with the solution dispensing assembly **420**. In this embodiment, the syringe pump is equivalent to that illustrated in FIG. **1**, except that the syringe pump assembly includes two actuators, actuator **425** and actuator **426**, that can pump liquid **160** to the respective needle arrays **405** and **406**.

Note the number of needles in needle array **405**, or needles in needle array **406**, and the syringe arrangement can be adjusted according to the application. The optimum distance between the individual needles needs to be maintained as previously disclosed. The holder can be specially manufactured (e.g. 3D printed or otherwise produced), to hold the syringe **415** and the syringe **416** in order to facilitate the pumping of oppositely charged solution **160** using the syringe pump.

A spinning drum **430** can be connected to ground **435** so that the drum **430** is kept at ground potential. A motor **440** can be connected to a drive shaft **445**. The motor **440** turns the spinning drum **430** at the desired rate. The oppositely charged solution **160** is dispensed from the needles in needle array **405** and needles in needle array **406** toward the rotating drum **430** where it collects as a fiber mat.

FIG. **5** illustrates another embodiment in which a thick fiber mat (as described with respect to previous embodiments) is produced using a syringeless spinneret system **500**. In some syringe-based mass production applications, the syringe needle can cause a bottleneck as the syringes clog. Such clogs waste time and create production overhead because frequent cleaning is necessary. As such, in the embodiments illustrated in FIG. **5A-C**, a syringeless spinneret system **500** is disclosed. The system **500** uses a rotating spindle **505** with a series of metallic spikes **510**, arranged in a helical pattern (or other pattern in other embodiments).

The rotating spindle **505** (and associated rotating helix of metallic spikes in spike array **510**) is held at a high +Ve potential with a power supply **115**. The rotating spindle **505** rotates inside a tank **515** filled with the desired solution **160**. The solid spike array **510** (e.g. solid needles) rotate through the solution **160**, picking up solution **160** as they pass.

As in other embodiments, a rotating drum **520** is connected to ground **525** and is held at ground potential. A motor **530** connected to drive shaft **535** can be used to turn the rotating drum **520**, where the fiber mat collects. Likewise, a motor **540** connected to a spindle shaft **545**, and drive shaft (not shown) can be used to turn the rotating spindle **505**.

The spindle **505** turns such that the solid spikes **510**, with liquid **160**, deposited thereon, rotate out of the tank **515** and generally toward an array of dry micro-tip needles **550** (necessary for the Corona discharge). The array of micro tip needles **550** can comprise tungsten (or other such metal).

The array of micro tip needles **550** can be maintained at high -kV potential with power supply **115**. The potential can be just below the air breakdown voltage. The micro-tip needle array **550** is used for -Ve ion production to neutralize positively charged nanofiber that collects on drum **520** and thereby facilitates a thicker mat.

The liquid **160** is attracted to the rotating drum **520** as a result of the potential difference. The liquid stream bridges the space between the solid spikes **510** and the rotating drum **520**, resulting in a nanofiber mat **125**. The high voltage, spiked spindle **505** can be electrically isolated from the motor **540** driving its rotation by an insulated coupler **555**. The insulated coupler **555** is configured to be long enough to prevent arching between the drive shaft (not shown) and the spindle shaft **545**.

The embodiments illustrated in FIGS. **5A-C** can be of particular value because nanofibers are increasingly used as functional textiles. In mass production applications, the system **500** can be used for depositing thicker nanofiber on an underlying non-conducting moving fabric.

For example, in FIG. **5B** an embodiment of a system **500** is illustrated, that takes advantage of a moving fabric. In the embodiment, a conveyor belt assembly **560** can be used. The conveyor belt assembly **560** includes a conveyor belt **570** comprising a rubber material or other non-conducting fabric. A ground plate **565** is fixed beneath the conveyor belt **560**. Nanofibers in solution **160**, attracted toward the ground plate **565**, are collected by the conveyor belt **560** (e.g. non-conducting fabric) moving in front of the ground plate **565**, while a set of negatively charge ions produced by corona discharge (as described herein) are directed to the top portion of the conveyor belt **560**.

FIG. **5C** illustrates a bottom view of the conveyor belt assembly **560**. The conveyor belt assembly **560** includes a housing **580** for the ground plate **565** which is connected to ground **525**. The housing **580** further holds a drive shaft **585** and a spinning shaft **590**. The drive shaft **585** is driven by motor **575** and is used to cycle the conveyor belt **570**.

FIG. **6A** illustrates another embodiment of a syringeless mass production system **600** for thick nanofiber mats **125**. In the system **600**, a circulation assembly **605** is used for continuously circulating solution **160** through conduit **620**. The conduit **620** connects to fluid input **690** that is fluidically connected to an internal groove **640** in dispenser **635**. The configuration is intended to prevent the solution **160** from drying in the dispenser **635**.

A pump **615**, which can be embodied as a peristaltic pump, is used to pump solution **160** from the solution tank **610** through the conduit **620**, to the dispenser **635**, out the fluid exit **691**, and back to the solution tank **610**. Such an enclosed design for solution flow overcomes the major problem of solution drying in syringeless electrospinning. In this embodiment, only a very small quantity of solution **160** is exposed to air, which prevents long term changes in concentration of the liquid **160**.

The conduit **620** can be connected to, and/or formed in, the dispenser **635** that encapsulates the rotating cylinder **625** with multiple solid needles or spikes, in a spike array **630**. The spikes in spike array **630** can be formed in even rows, in a helical pattern around the cylinder **625**, or in other patterns on the cylinder **625**.

Internal groove **640** is formed in the dispenser **635** along the path of the spikes in spike array **630**. The internal groove **640** can include slits **695**, so that the spikes can pick up solution **160** flowing through the groove **640**. FIG. **6C** provides a cut out view of the dispenser **635**.

Once the spikes in spike array **630** pick up solution **160** flowing through groove **640**, the rotation of cylinder **625** brings the spikes in spike array **630** to their top or upward pointing position, through slits **645** on the top surface of dispenser **635**, where the liquid is stretched into nanofiber. FIG. **6D** illustrates a cut away view of the cylinder **625** positioned in the dispenser **635**. FIG. **6E** illustrates the closed dispenser **635** with slits **645** exposing spikes in spike array **630** as the cylinder **625** rotates. The rotating cylinder **625** is driven by drive shaft **670** connected to motor **675**.

As in the other embodiments, the solution **160** on the tip of the spikes **630** is drawn to a rotating drum **650** (or a conveyor belt assembly **560**) by a potential difference. The rotating drum **650** is connected to ground **655** and is turned via a drive shaft **660** connected to a motor **665**. The rotating cylinder **625** can be held at a high positive kV potential with a dual power supply **115**.

The power supply **115** can be further connected to an array of one or more dry micro-tip needles **680** (necessary for the Corona discharge). The array of micro-tip needles **680** can comprise tungsten (or other such metal). The array of micro-tip needles **680** can be maintained at high -kV potential with power supply **115**. The potential can be just below the air breakdown voltage. The micro-tip needle array **680** is used for -Ve ion production to neutralize positively charged nanofiber that collects on drum **650** and thereby facilitate a thicker mat of material **125**.

The system **600** further includes a cleaning material **685** formed in the dispenser **635**, formed in the path of the spikes in spike array **630** as they return to internal groove **640**, as illustrated in FIG. **6B**. The cleaning material **685** can comprise a soft material that wipes the residual fluid from the spikes in the spike array **630**. The cleaning material **685** is arranged such that the rotating spike array **630** brushes against the cleaning material **685** while rotating, so as to prevent formation of any solid layer of solution on the spikes in spike array **630**.

The system **600** provides circulation that prevents the solution **160** from drying in the dispenser **635**. In addition, after some amount of electrospinning, the density of the solution changes which can result in larger nanofibers. The disclosed circulation provided by system **600** through the narrow internal grooves, results in limited exposure to air, thereby maintaining a more stable solution **160** density. Finally, the soft cleaning material **685** is provided so that the spikes **630** do not accumulate solution **160**, which can solidify over time.

FIG. **7** illustrates a flow chart illustrating steps associate with a method **700** for fabricating fiber mats with electrospinning. The method begins at step **705**. At step **710**, an electrospinning system, in accordance with any of the embodiments disclosed herein, can be configured. The electrospinning system can take advantage of a dual polarity source as disclosed in the various systems detailed herein. At step **715**, a solution can be created for the desired mat fiber material. Possible precursor solutions include Alumina→Aluminum 2,4-pentadionate+Aceton, Zirconia→Zirconium Carbonate+Acetic Acid, WO₃→Ammonium metatungstate+D.I. Water, and TiO₂→Titanium Isopropoxide. These solutions can be added with polymeric solution containing approximately 5-8 wt % of polyvinylpyrrolidone in Acetone or Ethanol.

Once the solution is ready, a high positive potential can be supplied to the solution dispensing arrangement at step **720**. As disclosed herein, in some embodiments, the solution dispensing arrangement can be one or more needles. In other embodiments, the solution dispensing arrangement can com-

11

prise a rotating spindle with associated solid needles or spikes that are dipped into a pool of solution. The rotating drum collector can be grounded as shown at step 725, and a high negative potential can be supplied to a knife edge or needle arrangement as illustrated at step 730 to facilitate Corona discharge, resulting in a thicker fiber mat.

As shown at step 735, the liquid solution is attracted to the rotating drum by the potential difference. As the liquid passes through the air, it is pulled into a fiber that is collected on the rotating drum as shown at step 740, resulting in a fiber mat. The process continues until the fiber mat is of a desired thickness as shown at step 745, at which point the method ends at step 750.

The embodiments disclosed herein provide a much smaller, lighter weight, and simpler electrospinning device than previously known in the art. The embodiments are much safer to use as they can limit the output power to only a few watts, and can be operated with a 9V battery as well as a 12V DC adapter. The systems and methods disclosed herein further provide a versatile production unit that employs a syringe needled spinneret for prototype nanofiber production, and a needleless helical spinneret for mass production. The embodiments can be used to create thicker ceramic or polymeric nanofiber mats, as compared to prior art approaches, using a specially designed Corona ionizer.

Based on the foregoing, it can be appreciated that a number of embodiments, preferred and alternative, are disclosed herein. In an embodiment, an electrospinning system comprises a power supply, a solution dispensing assembly held at positive potential by the power supply, a Corona discharge assembly held at negative potential by the power supply, and a collector wherein a solution is drawn from the solution dispensing assembly to the collector forming a fiber mat thereon.

In an embodiment, the solution dispensing assembly comprises at least one dispensing needle, a manifold attached to a syringe, the manifold connecting the syringe to the at least one dispensing needle, and a syringe pump for pumping the solution to the at least one dispensing needle. In an embodiment the solution dispensing assembly comprises a solution tank containing the solution, a rotating spindle, at least one solid needle on the rotating spindle, and a motor for rotating the spindle.

In an embodiment, the Corona discharge assembly comprises a plate with a knife edge. In an embodiment the Corona discharge assembly comprises an array of at least one micro-tipped needle.

In an embodiment the collector comprises a drum collector. In an embodiment a ground is connected to the drum collector. In an embodiment the collector comprises a conveyor belt assembly. In an embodiment the conveyor belt assembly further comprises a ground plate, the ground plate being held at ground potential, and a conveyor belt wrapping around the ground plate.

In an embodiment, the power supply comprises a dual polarity power supply.

In another embodiment, an apparatus comprises a dual polarity power supply, a solution dispensing assembly held at positive potential by the dual polarity power supply, a Corona discharge assembly held at negative potential by the dual polarity power supply, and a collector wherein a solution is drawn from the solution dispensing assembly to the collector forming a fiber mat thereon.

In an embodiment, the solution dispensing assembly comprises at least one dispensing needle, a manifold attached to a syringe, the manifold connecting the syringe to

12

the at least one dispensing needle, and a syringe pump for pumping the solution to the at least one dispensing needle.

In an embodiment, the solution dispensing assembly comprises a solution tank containing the solution, a rotating spindle, at least one solid needle on the rotating spindle, and a motor for rotating the spindle.

In an embodiment the Corona discharge assembly comprises a plate with a knife edge. In an embodiment the Corona discharge assembly comprises an array of at least one micro-tipped needle.

In an embodiment the collector comprises a drum collector connected to a ground. In an embodiment the collector comprises a ground plate, the ground plate being held at ground potential, and a conveyor belt wrapping around the ground plate.

In yet another embodiment, method comprises holding a solution associated with a solution dispensing assembly at positive potential with a power supply, holding a Corona discharge assembly at negative potential by the power supply, and collecting a fiber mat on a collector wherein the solution is drawn from the solution dispensing assembly to the collector according to a potential difference.

In an embodiment the method comprises turning the collector with a motor, the collector comprising a drum collector.

In an embodiment the power supply comprises a dual polarity power supply.

It will be appreciated that variations of the above-disclosed and other features and functions, or alternatives thereof, may be desirably combined into many other different systems or applications. Also, various presently unforeseen or unanticipated alternatives, modifications, variations or improvements therein may be subsequently made by those skilled in the art which are also intended to be encompassed by the following claims.

What is claimed is:

1. An electrospinning system comprising:

a power supply;

a circulation assembly connected to the power supply, the circulation assembly comprising:

a dispenser;

a plurality of spikes arranged in a helical pattern and held at a potential by the power supply, at least one spike affixed to a rotating cylinder; and

a conduit configured to allow a solution to flow through the dispenser wherein the solution is deposited on the plurality of spikes; and

a collector wherein the solution is drawn from the plurality of spikes to the collector via a potential difference between the dispenser and collector, forming a fiber mat on the collector.

2. The electrospinning system of claim 1 wherein the circulation assembly comprises:

a solution tank;

a pump;

a conduit connecting the pump to the dispenser; and

an exit from the dispenser connecting the dispenser back to the solution tank.

3. The electrospinning system of claim 2 wherein the circulation assembly comprises:

at least one internal groove formed in the dispenser, wherein the at least one spike affixed to the rotating cylinder passes through the internal groove to contact the solution.

4. The electrospinning system of claim 3 wherein the circulation assembly comprises:

13

- at least one slit formed in the dispenser, wherein the at least one spike affixed to the rotating cylinder passes through the slit.
5. The electrospinning system of claim 1 further comprising:
5 an array of one or more dry micro-tip needles beyond the collector.
6. The electrospinning system of claim 1 wherein each of the at least one spikes comprise needles.
7. The electrospinning system of claim 1 further comprising:
10 a motor and a drive shaft configured to rotate the rotating cylinder.
8. The electrospinning system of claim 1 wherein the collector comprises a drum collector.
9. The electrospinning system of claim 8 further comprising:
15 a ground connected to the drum collector.
10. The electrospinning system of claim 1 wherein the collector comprises a conveyor belt assembly.
11. The electrospinning system of claim 1 wherein the power supply comprises a dual polarity power supply.
12. An apparatus comprising:
20 a dual polarity power supply;
a circulation assembly connected to the power supply, the circulation assembly comprising:
25 a dispenser;
a plurality of spikes arranged in a helical pattern and held at a potential by the power supply, affixed to a rotating cylinder held at a potential by the dual polarity power supply; and
30 a conduit configured to allow a solution to flow through the dispenser wherein the solution is deposited on the plurality of spikes; and
a collector held at an opposite potential by the dual polarity power supply the solution is drawn from the plurality of spikes to the collector forming a fiber mat on the collector.
13. The apparatus of claim 12 wherein the circulation assembly comprises:
40 a solution tank;
a pump;
a conduit connecting the pump to the dispenser;

14

- an exit from the dispenser connecting the dispenser back to the solution tank;
- at least one internal groove formed in the dispenser, wherein the at least one spike affixed to the rotating cylinder passes through the internal groove to contact the solution; and
- at least one slit formed in the dispenser, wherein the at least one spike affixed to the rotating cylinder passes through the slit.
14. The apparatus of claim 12 further comprising:
an array of one or more dry micro-tip needles beyond the collector.
15. The apparatus of claim 12 wherein each of the at least one spikes comprise needles.
16. The apparatus of claim 12 further comprising:
15 a motor and a drive shaft configured to rotate the rotating cylinder.
17. The apparatus of claim 12 wherein the collector comprises at least one of:
20 a drum collector; and
a conveyor belt assembly.
18. A method comprising:
holding a solution associated with a circulation assembly at a potential with a dual polarity power supply, the circulation assembly comprising: a dispenser, a plurality of spikes arranged in a helical pattern affixed to a rotating cylinder held at a potential by the dual polarity power supply, and a conduit configured to allow a solution to circulate through the dispenser and a solution tank;
30 holding a collector at an opposite potential with the dual polarity power supply; and
collecting a fiber mat on a collector wherein the solution is drawn from the circulation assembly to the collector according to a potential difference.
19. The method of claim 18 further comprising:
turning the collector with a motor, the collector comprising a drum collector.
20. The method of claim 18 wherein the dual polarity power supply is configured to operate at 4 watts of output power while maintaining a 0 to 40 kV DC and 0 to -20 kV DC output in dual polarity mode.

* * * * *