

US009499882B2

(12) **United States Patent**
Wallace et al.

(10) **Patent No.:** **US 9,499,882 B2**
(45) **Date of Patent:** **Nov. 22, 2016**

(54) **STRAIN-DETECTING COMPOSITE MATERIALS**

(75) Inventors: **Terryl A. Wallace**, Yorktown, VA (US); **Stephen W. Smith**, Newport News, VA (US); **Robert S. Piascik**, Williamsburg, VA (US); **Michael R. Horne**, Yorktown, VA (US); **Peter L. Messick**, Poquoson, VA (US); **Joel A. Alexa**, Hampton, VA (US); **Edward H. Glaessgen**, Yorktown, VA (US); **Benjamin T. Hailer**, Rome, NY (US)

(73) Assignee: **UNITED STATES OF AMERICA AS REPRESENTED BY THE ADMINISTRATOR OF THE NATIONAL AERONAUTICS AND SPACE ADMINISTRATION**, Washington, DC (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 1548 days.

(21) Appl. No.: **12/685,280**

(22) Filed: **Jan. 11, 2010**

(65) **Prior Publication Data**

US 2010/0190026 A1 Jul. 29, 2010

Related U.S. Application Data

(60) Provisional application No. 61/143,481, filed on Jan. 9, 2009.

(51) **Int. Cl.**

B32B 15/00 (2006.01)

C22C 1/04 (2006.01)

B22F 5/00 (2006.01)

(52) **U.S. Cl.**

CPC **C22C 1/0416** (2013.01); **B22F 5/006** (2013.01); **B22F 2998/00** (2013.01); **B22F 2999/00** (2013.01); **Y10T 428/12132** (2015.01)

(58) **Field of Classification Search**

USPC 428/546, 553, 567, 651
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,209,568 A * 5/1993 Buffard et al. 374/49
5,508,116 A * 4/1996 Barrett 428/567

(Continued)

OTHER PUBLICATIONS

Yi et al., "Fracture toughening mechanism of shape memory alloys due to martensite transformation", Sep. 18, 2000, Int'l J. of Solids and Structures, vol. 37, Issue 38, pp. 5315-5327.*

Porter et al., ("Fatigue and fracture behavior of nickel-titanium shape-memory alloy reinforced aluminum composites"), 2001, Materials Science and Engineering, vol. A314, pp. 186-193.*

(Continued)

Primary Examiner — David Sample

Assistant Examiner — Lucas Wang


(74) *Attorney, Agent, or Firm* — Robin W. Edwards;
Andrea Z. Warmbier

(57) **ABSTRACT**

A composite material includes a structural material and a shape-memory alloy embedded in the structural material. The shape-memory alloy changes crystallographic phase from austenite to martensite in response to a predefined critical macroscopic average strain of the composite material. In a second embodiment, the composite material includes a plurality of particles of a ferromagnetic shape-memory alloy embedded in the structural material. The ferromagnetic shape-memory alloy changes crystallographic phase from austenite to martensite and changes magnetic phase in response to the predefined critical macroscopic average strain of the composite material. A method of forming a composite material for sensing the predefined critical macroscopic average strain includes providing the shape-memory alloy having an austenite crystallographic phase, changing a size and shape of the shape-memory alloy to thereby form a plurality of particles, and combining the structural material and the particles at a temperature of from about 100-700° C. to form the composite material.

36 Claims, 4 Drawing Sheets

10, 110



12

14, 114

(56)

References Cited

U.S. PATENT DOCUMENTS

6,200,643 B1 * 3/2001 Sugai et al. 427/475
7,393,595 B2 * 7/2008 Chandrasekaran et al. .. 428/614
2003/0221411 A1 * 12/2003 Nesbitt et al. 60/204
2011/0008643 A1 * 1/2011 Shaw et al. 428/592

OTHER PUBLICATIONS

Liu et al., “An Investigation on the Interface in a NiTi Short-Fiber-Reinforced 6061 Aluminum Composite by Transmission Electron Microscope”, Nov. 2008, Metallurgical and Materials Transactions A, vol. 39A, pp. 2749-2759.*

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6

STRAIN-DETECTING COMPOSITE MATERIALS

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of U.S. Provisional Patent Application No. 61/143,481, filed on Jan. 9, 2009, which is hereby incorporated by reference in its entirety.

This invention was made in part by employees of the United States Government and may be manufactured and used by or for the Government of the United States of America for governmental purposes without the payment of any royalties thereon or therefor.

TECHNICAL FIELD

The present invention generally relates to composite materials, and more specifically, to strain-detecting composite materials.

BACKGROUND OF THE INVENTION

Nondestructive evaluation (NDE) techniques are generally useful for evaluating properties of a material without causing damage to the material. For example, NDE techniques are often used to detect overload strain, fatigue damage, and/or localized strain in structural components of airframes. In particular, NDE techniques including fiber optic strain sensing and resistance strain gages may be useful for mapping strain fields in such components. Other NDE techniques based on eddy currents and electromagnetic induction may also non-invasively detect real-time fatigue and/or failure without disturbing the airframe and/or component. Acoustic monitoring, another NDE technique, may also be useful for detecting acoustic emissions produced within a material under strain. Alternatively, giant magneto resistance sensors may be used to measure magnetic fields and magnetic properties of materials. Existing efforts to improve strain-detection focus on improvements in the aforementioned NDE techniques, rather than on the response of the material of the structural component.

SUMMARY OF THE INVENTION

The composite material includes a structural material and a shape-memory alloy embedded in the structural material. The shape-memory alloy changes crystallographic phase from austenite to martensite in response to a predefined critical macroscopic average strain of the composite material.

In a second embodiment, the composite material includes a plurality of particles of a ferromagnetic shape-memory alloy embedded in the structural material. The ferromagnetic shape-memory alloy changes crystallographic phase from austenite to martensite and changes magnetic phase in response to the predefined critical macroscopic average strain of the composite material.

A method of forming a composite material for sensing a predefined critical macroscopic average strain includes providing the structural material in powder form and providing the shape-memory alloy having an austenite crystallographic phase. The shape-memory alloy changes crystallographic phase from austenite to martensite in response to the predefined critical macroscopic average strain of the composite material. The method also includes changing a size and shape of the shape-memory alloy to thereby form a

plurality of particles and combining the structural material and the plurality of particles of the shape-memory alloy at a temperature of from about 100° C. to about 700° C. to thereby form the composite material including the plurality of particles embedded in the structural material.

The methods provide composite materials that optimize existing nondestructive evaluation (NDE) techniques for detecting strain of airframes and/or components thereof. That is, the composite materials allow proactive, rather than reactive, strain-detection. Additionally, the composite materials allow for both ground-based and in-flight inspection. Therefore, the composite materials minimize costly and time-consuming detailed inspections and down-time of airframes and structural components, and minimize premature component replacement. Further, the composite materials minimize aircraft complexity and weight, and allow for detection of comparatively smaller strain at comparatively earlier stages of fatigue than existing composite or structural materials. The composite materials may also reduce existing airframe design constraints, since physical access to each component of the airframe strain-detection may no longer be necessary. Such reduced design constraints may allow for comparatively larger payloads, increased service life, and less restriction on mission requirements as compared to airframes formed from existing composite or structural materials.

The above features and advantages and other features and advantages of the present invention are readily apparent from the following detailed description of the best modes for carrying out the invention when taken in connection with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a reproduction of an optical micrograph of a cross-section of a composite material;

FIG. 2 is a graphical representation of a relationship between strain and temperature for a shape-memory alloy of the composite material of FIG. 1;

FIG. 3 is an illustration of a response of the shape-memory alloy to a crack in the composite material of FIG. 1 in response to a predefined critical macroscopic average strain;

FIG. 4 is an illustration of a laminate embodiment of the composite material;

FIG. 5 is an illustration of the shape-memory alloy applied as a coating; and

FIG. 6 is an illustration of a shape-memory alloy applied as a coating at areas of high strain concentration.

DETAILED DESCRIPTION OF THE INVENTION

Referring to the drawings, wherein like reference numerals refer to like components, a composite material is shown generally at **10** in FIG. 1. The composite material **10** may be useful for aeronautical and aerospace applications, such as airframes and/or structural components thereof. For example, the composite material **10** may be a metal, and may form at least a portion of an airframe, such as, but not limited to, a fuselage, a load-bearing strut, and/or a wing. However, it is to be appreciated that the composite material **10** may also be useful for other applications, such as, but not limited to, construction, rail, automotive, and marine applications.

Referring to FIG. 1, the composite material **10** includes a structural material **12**. As used herein, the terminology “structural material” refers to ceramics, polymers, alloys,

i.e., partial or complete solid solutions of one or more elements in a metallic matrix, and any combinations of ceramics, polymers, and alloys which are useful for structural applications. That is, the structural material **12** may be, for example, a non-magnetic metal, and may possess sufficient strength and malleability to be useful for forming airframes and/or structural components thereof, such as, but not limited to, struts, l-beams, supports, and the like. Suitable structural materials include, but are not limited to, structural magnesium alloys, structural aluminum alloys, structural steel alloys, and combinations thereof.

A skilled artisan generally selects the structural material **12** according to a desired application and expected strain and/or loading of the composite material **10**. That is, a structural component and/or airframe formed from the composite material **10** may be subject to stress, which is a load applied to a unit area of the composite material **10**. Exemplary stress applied to the composite material **10** may be characterized as tension, compression, torsion, shear, bending, and combinations thereof, and may be cycling, monotonic, and combinations thereof. Such stress produces a strain, i.e., a deformation deflection gradient in the composite material **10**. Further, at a critical macroscopic average strain ϵ_c , the stress typically induces a crack, fissure, plastic deformation, wear, breakage, fatigue, or other damage signal in the structural component. Therefore, for airframe applications, the structural material **12** may be selected based on an ability to withstand in-flight and/or ground-based strain. Generally, the structural material **12** may have a yield strength of from about 100 to about 1,000 MPa.

The structural material **12** may be present in the composite material **10** in an amount of at least 40 parts by volume based on 100 parts by volume of the composite material **10**. For example, the structural material **12** may be present in the composite material **10** in an amount of 90 parts by volume based on 100 parts by volume of the composite material.

The structural material **12** may be formed of, i.e., alloyed from, any suitable constituent. For example, the structural material **12** may include metallic alloys such as beryllium, titanium, nickel, copper, iron, carbon, manganese, chromium, vanadium, tungsten, zinc, magnesium, silicon, and combinations thereof. In one example, the structural material **12** may be aluminum. Particular suitable aluminum structural materials include, but are not limited to, 7075 aluminum, 6061 aluminum, 6063 aluminum, 2024 aluminum, and 5052 aluminum.

Referring again to FIG. 1, the composite material **10** includes a shape-memory alloy **14** embedded in the structural material **12**. As used herein, the terminology "shape-memory alloy" refers to alloys which exhibit a shape-memory effect. That is, the shape-memory alloy **14** may undergo a solid state phase change via molecular rearrangement to shift between a martensite phase, i.e., "martensite", and an austenite phase, i.e., "austenite". Stated differently, the shape-memory alloy **14** may undergo a displacive transformation rather than a diffusional transformation to shift between martensite and austenite. In general, the martensite phase refers to the comparatively lower temperature phase and is often more deformable than the comparatively higher temperature austenite phase. As the shape-memory alloy **14** is cooled, molecules of the shape-memory alloy **14** rearrange from a body-centered cubic arrangement, i.e., the austenite phase, to a face-centered cubic, tetragonal, or hexagonal arrangement, i.e., the martensite phase. The temperature at which the shape-memory alloy **14** begins to change from the austenite phase to the martensite phase is known as the martensite start temperature, M_s . The temperature at which

the shape-memory alloy **14** completes the change from the austenite phase to the martensite phase is known as the martensite finish temperature, M_f . Similarly, as the shape-memory alloy **14** is heated, the temperature at which the shape-memory alloy **14** begins to change from the martensite phase to the austenite phase is known as the austenite start temperature, A_s . The temperature at which the shape-memory alloy **14** completes the change from the martensite phase to the austenite phase is known as the austenite finish temperature, A_f .

Although the shape-memory alloy **14** changes crystallographic phase in response to temperature, the transformation, i.e., the change in crystallographic phase, may also be a function of strain of the shape-memory alloy **14**, as set forth in more detail below. The shape-memory alloy **14** may be present in the composite material **10** for strain-detection. That is, the shape-memory alloy **14** may undergo a crystallographic phase change upon exposure to strain. Non-destructive evaluation (NDE) techniques such as acoustic monitoring, fiber optic strain sensing, eddy current techniques based on electromagnetic induction, and/or giant magneto resistance sensing may detect the crystallographic phase change, as set forth in more detail below.

The shape-memory alloy **14** may be present in the composite material **10** in an amount of from about 5 to about 60 parts by volume based on 100 parts by volume of the composite material **10**. For example, the shape-memory alloy **14** may be present in the composite material **10** in an amount of less than or equal to about 25 parts by volume, generally about 10 parts by volume, based on 100 parts by volume of the composite material **10**.

The shape-memory alloy **14** may include an element selected from the group of cobalt, nickel, titanium, indium, manganese, iron, palladium, zinc, copper, silver, gold, cadmium, tin, silicon, platinum, gallium, and combinations thereof. For example, suitable shape-memory alloys **14** may include nickel-titanium alloys, nickel-cobalt-aluminum alloys, copper alloys, nickel-manganese-gallium, and the like. Suitable shape-memory alloys **14** may be binary, ternary, or any order as long as the shape-memory alloy **14** may change from austenite to martensite, as set forth in more detail below. A skilled artisan may select the shape-memory alloy **14** according to desired operating temperatures of the composite material **10**, also as set forth in more detail below.

Referring again to FIG. 1, the shape-memory alloy **14** may be present in the composite material **10** in the form of particles, e.g., a plurality of particles. The particles of the shape-memory alloy **14** may have any suitable shape. For example, the particles may be irregularly-shaped. The particles may be circular, spherical, flat, folded, ellipsoidal, crenulated, rectangular, oval, triangular, and combinations thereof. Further, the particles may have any suitable form. For example, the particles may be present in the composite material **10** in disk-, flake-, pellet-, fiber- and/or powder-form.

Referring to FIG. 1, the shape-memory alloy **14** is embedded in the structural material **12**. That is, the structural material **12** may at least partially encapsulate and surround the shape-memory alloy **14**. It is to be appreciated, however, that one or more particles of the shape-memory alloy **14** may protrude through a visible edge of the composite material **10**, e.g., when the composite material **10** is initially formed and/or cross-sectioned. Additionally, the particles may have any orientation within the structural material **12**, and the particles may have any suitable size. In one variation, the particles of the shape-memory alloy **14** may have an average particle diameter of from about 10 to about 100 μm . It is to

5

be appreciated that the size, shape, and/or orientation of each particle may be the same or different than the size, shape, and/or orientation of another particle.

The shape-memory alloy **14** may be substantially chemically bonded to the structural material **12**. That is, the shape-memory alloy **14** may not only be mechanically bonded to the structural material **12**, i.e., adjacent to and in contact with the structural material **12**, but may also be substantially chemically bonded to the structural material **12**. Stated differently, the shape-memory alloy **14** may form chemical bonds with the surrounding structural material **12** in the composite material **10**. Without intending to be limited by theory, chemical bonding between the structural material **12** and the shape-memory alloy **14** may minimize debonding and imperfect mechanical bonds that affect an internal strain distribution of a particle when the particle is exposed to increasing strain. Such internal strain distribution of a particle affects a volume of the particle undergoing a crystallographic phase change under a given strain. Although each particle of the shape-memory alloy **14** is preferably substantially chemically bonded to the structural material **12**, it is to be appreciated that some particles may also be partially debonded to the structural material **12**.

In operation, i.e., for strain-detection, the shape-memory alloy **14** changes crystallographic phase from austenite to martensite in response to a predefined critical macroscopic average strain ϵ_c of the composite material **10**. As used herein, the terminology “predefined critical macroscopic average strain” is a value of strain sufficient to induce deformation and/or failure in a component formed from the composite material **10** that is subjected to either monotonic or cycling loading. For example, the predefined critical macroscopic average strain ϵ_c may be a value of strain known to cause cracks, fissures, plastic deformation, wear, breakage, fatigue, and/or other damage in a structural component and/or airframe formed from the composite material **10**.

More specifically, the predefined critical macroscopic average strain ϵ_c may occur, i.e., may be applied to the composite material **10**, at a temperature, T , of greater than or equal to about the martensite start temperature, M_s , of the shape-memory alloy **14** and less than about the austenite start temperature, A_s , of the shape-memory alloy **14**. That is, the shape-memory alloy **14** may generally be in the austenitic phase for a range of loads, and corresponding strain values, applied to the composite material **10**.

However, referring to FIG. 2, as the strain (indicated by arrow B) increases to the predefined critical macroscopic average strain (indicated by point ϵ_c) at the martensite start temperature, M_s , of the shape-memory alloy **14** (FIG. 1), the shape-memory alloy **14** transforms, i.e., changes crystallographic phase, from austenite to martensite in response to the predefined critical macroscopic average strain ϵ_c . That is, at the predefined critical macroscopic average strain ϵ_c , the temperature, T , at which the load is applied is greater than or equal to the martensite start temperature, M_s , and the shape-memory alloy **14** transforms to martensite. Suitable temperatures, T , at which the load may be applied range from about -150° F. to about 500° F. For example, for airframes and/or components thereof, the composite material **10** may change crystallographic phase in response to the predefined critical macroscopic average strain ϵ_c applied at a temperature, T , of from about -40° F. to about 150° F.

Upon transformation from austenite to martensite at the predefined critical macroscopic average strain ϵ_c , the shape-memory alloy **14** may generate an acoustic emission in response to the predefined critical macroscopic average

6

strain, ϵ_c . The acoustic emission is a phenomenon whereby external stimuli, e.g., loading, generates elastic waves. Acoustic emissions generally occur during a surface displacement of the composite material **10** due to energy waves generated upon a rapid release of localized stress energy of the shape-memory alloy **14**. Therefore, acoustic emissions are a type of signature given off by the shape-memory alloy **14** upon loading to the predefined critical macroscopic average strain ϵ_c that may be measured and/or monitored by NDE techniques such as acoustic monitoring.

In particular, the shape-memory alloy **14** may generate an acoustic emission in response to the predefined critical macroscopic average strain ϵ_c that is greater in magnitude than an acoustic emission of the structural material **12**. That is, the presence of the particles of the shape-memory alloy **14** may not affect the structural characteristics and/or crystallographic phase of the structural material **12**. Stated differently, the structural material **12** may not change crystallographic phase in response to the predefined critical macroscopic average strain ϵ_c .

Referring to FIG. 3, acoustic monitoring may then detect the acoustic emission of the shape-memory alloy **14** to locate, for example, a growth of a crack **18** formed in the composite material **10** due to a previously-applied or presently-applied load that generates a strain at or above the predefined critical macroscopic average strain ϵ_c . For example, and with reference to FIG. 3, as the crack **18** forms in the composite material **10** in response to the predefined critical macroscopic average strain ϵ_c , the crack **18** advances at a crack tip process zone **20**. Particles of the shape-memory alloy **14** within the crack tip process zone **20** may undergo the crystallographic phase change from austenite to martensite and generate the acoustic emission, indicated by concentric circles AE in FIG. 3. Therefore, the crystallographic phase change of the shape-memory alloy **14** in the composite material **10** indicates that the predefined critical macroscopic average strain ϵ_c has been reached for the structural component and/or airframe formed from the composite material **10**. The acoustic emission AE may then be detected by known NDE acoustic monitoring techniques.

Referring to FIG. 3, it is to be appreciated that at least one, but not necessarily all, of the particles of the shape-memory alloy **14** may change crystallographic phase in response to the predefined critical macroscopic average strain ϵ_c . That is, particles located within or near the crack tip process zone **20**, may change crystallographic phase, whereas other particles may not. However, depending on a severity of the crack **18**, all particles may change crystallographic phase. Stated differently, the number and location of particles that undergo the crystallographic phase change at the predefined critical macroscopic average strain ϵ_c may vary as a result of average strain or localized strain gradient, i.e., cracks **18**. Referring to FIG. 3, the crack tip process zone **20** may evoke the crystallographic phase change (indicated by cross-hatching PC of the particles of the shape-memory alloy **14** in FIG. 3) in only a localized region near the crack **18**, whereas the crystallographic phase of particles outside of the propagating crack tip process zone **20** may remain unchanged.

As set forth above, the acoustic emission AE shown in FIG. 3 may be detected by NDE acoustic monitoring techniques. For example, a sensor on-board an aircraft or spacecraft may detect the acoustic emission AE corresponding to the crystallographic phase change of one or more particles of the shape-memory alloy **14** in-flight, and warn an operator in real-time that the predefined critical macroscopic average

strain ϵ_c has been reached. Likewise, the acoustic emission AE may be recorded for future evaluation and/or ground-based inspection.

Notably, however, the composite material **10** including the shape-memory alloy **14** may also be useful for ground-based inspection of the airframe and/or structural component. That is, with reference to FIG. 3, since the temperature at which the load is applied, T , is greater than or equal to about the martensite start temperature, M_s , of the shape-memory alloy **14** and less than about the austenite start temperature, A_s , of the shape-memory alloy **14**, the shape-memory alloy **14** may not revert to austenite from martensite. That is, referring to FIG. 2, the particles of the shape-memory alloy **14** may remain in the martensite phase upon unloading after the predefined critical macroscopic average strain ϵ_c is reached, since the temperature at which the load is applied, T , is less than the austenite start temperature, A_s , of the shape-memory alloy **14**. Therefore, a ground-based inspection of the airframe and/or structural component may also indicate that the composite material **10** has been exposed to the predefined critical macroscopic average strain ϵ_c .

Further, in one variation, the shape-memory alloy **114** may be a ferromagnetic shape-memory alloy. That is, without intending to be limited by theory, the ferromagnetic shape-memory alloy **114** may produce a magnetic field and exhibit ferromagnetic properties such as parallel alignment of electrons of the ferromagnetic shape-memory alloy **114** when exposed to a magnetic field. More specifically, ferromagnetism generally results from an internal molecular field that acts on and aligns individual electron spins spontaneously into alignment regions, i.e., domains. Further, unpaired electrons in ferromagnetic materials, e.g., iron, cobalt, and nickel, are generally not in an outermost electron orbital, and are thus shielded from unpaired electrons of other atoms. Such unpaired electrons generally do not align anti-parallel, but rather align in parallel to create a net magnetic moment. Therefore, the ferromagnetic shape-memory alloy **114** may change magnetic state, e.g., from and/or to a paramagnetic state and a ferromagnetic state, upon exposure to the predefined critical macroscopic average strain ϵ_c . Suitable ferromagnetic shape-memory alloys may include, but are not limited to, CoNiAl, Ni₂MnGa, Ni₂MnAl, Fe—Pd, Fe₃Pt, NiTi, CuZnAl, CuAlNi, and combinations thereof.

In a second embodiment, the composite material **110** includes the structural material **12** and a plurality of particles of the ferromagnetic shape-memory alloy **114** embedded in the structural material **12**. In this embodiment, the ferromagnetic shape-memory alloy **114** changes crystallographic phase from austenite to martensite in response to the predefined critical macroscopic average strain ϵ_c of the composite material **110**. As set forth above, the predefined critical macroscopic average strain ϵ_c may occur at a temperature, T , of greater than or equal to about the martensite start temperature, M_s , of the ferromagnetic shape-memory alloy **114** and less than about the austenite start temperature, A_s , of the ferromagnetic shape-memory alloy **114**. Further, the ferromagnetic shape-memory alloy **114** may not revert to austenite from martensite.

However, in this embodiment, the ferromagnetic shape-memory alloy **114** also changes magnetic phase in response to the predefined critical macroscopic average strain ϵ_c of the composite material **110**. For example, the ferromagnetic shape-memory alloy **114** may change from a paramagnetic phase to a diamagnetic phase in response to the predefined critical macroscopic average strain ϵ_c . That is, without

intending to be limited by theory, above a Curie temperature, T_c , the ferromagnetic shape-memory alloy **114** is generally magnetic, and below the Curie temperature, T_c , the ferromagnetic shape-memory alloy **114** is generally non-magnetic.

If the temperature, T , at which a load corresponding to the predefined critical macroscopic average strain ϵ_c is increased to the Curie temperature, T_c , thermal motion overwhelms any unpaired electron alignment and magnetization may disappear. Likewise, if T is below T_c , magnetization may remain after a magnetic field is removed. Because electron alignment is a function of atomic distances, the Curie temperature, T_c , is also a function of strain.

Therefore, a composition of the ferromagnetic shape-memory alloy **114** may be selected such that the martensite start temperature, M_s , may be approximately equal to the Curie temperature, T_c . In particular, for a given composition of the ferromagnetic shape-memory alloy **114**, the martensite start temperature, M_s , may be below the temperature, T , at which the load is applied for a range of loads. However, at the predefined critical macroscopic average strain ϵ_c , the temperature, T , at which the load is applied may equal the martensite start temperature, M_s , of the ferromagnetic shape-memory alloy **114**. Therefore, the ferromagnetic shape-memory alloy **114** changes crystallographic phase and magnetic phase in response to the predefined critical macroscopic average strain ϵ_c of the composite material **110**.

Referring again to FIG. 3, upon transformation from austenite to martensite at the predefined critical macroscopic average strain ϵ_c , the ferromagnetic shape-memory alloy **114** changes magnetic phase in response to the predefined critical macroscopic average strain ϵ_c . The magnetic phase change may be measured and/or monitored by NDE techniques such as giant magneto resistance sensing.

In particular, the ferromagnetic shape-memory alloy **114** may change magnetic phase in response to the predefined critical macroscopic average strain ϵ_c , while the surrounding structural material **12** may not change magnetic phase. Referring to FIG. 3, a giant magneto resistance sensor may then detect the magnetic phase change of the ferromagnetic shape-memory alloy **114** to locate, for example, a crack formed in the composite material **110** due to a previously-applied or presently-applied load that generated a strain at or above the predefined critical macroscopic average strain ϵ_c . For example, with reference to FIG. 3 and as set forth above, as the crack **18** forms in the composite material **110** in response to the predefined critical macroscopic average strain ϵ_c , the crack **18** advances at the crack tip process zone **20**. Particles of the ferromagnetic shape-memory alloy **114** within the crack tip process zone **20** may undergo the magnetic phase change, indicated by cross-hatching PC in FIG. 3. Therefore, the magnetic phase change of the ferromagnetic shape-memory alloy **114** in the composite material **110** indicates that the predefined critical macroscopic average strain ϵ_c has been reached for the structural component and/or airframe formed from the composite material **110**. The magnetic phase change may then be detected by known NDE monitoring techniques, such as giant magneto resistance sensing.

Referring to FIG. 3, it is to be appreciated that at least one, but not all, of the particles of the ferromagnetic shape-memory alloy **114** may change magnetic phase in response to the predefined critical macroscopic average strain ϵ_c . That is, particles located within or near the crack tip process zone **20**, may change magnetic phase, while other particles may not. However, depending on a severity of a strain field associated with the crack **18**, all particles may change

magnetic phase. Stated differently, the number and location of particles that undergo the magnetic phase change at the predefined critical macroscopic average strain ϵ_c may vary as a result of localized strain gradient, i.e., cracks **18**. Referring to FIG. **3**, the crack tip process zone **20** may evoke the magnetic phase change in only a localized region, indicated by cross-hatching PC of the particles, near the crack **18**, whereas the crystallographic phase of particles outside of the propagating crack tip process zone **20** may remain unchanged.

As set forth above, the magnetic phase change indicated in FIG. **3** may be detected by NDE sensing techniques. For example, a sensor on-board an aircraft or spacecraft may detect the magnetic phase change corresponding to the predefined critical macroscopic average strain ϵ_c of one or more particles of the ferromagnetic shape-memory alloy **114** in flight and warn an operator that the predefined critical macroscopic average strain ϵ_c has been reached. Likewise, the composite material **110** including the ferromagnetic shape-memory alloy **114** may also be useful for ground-based inspection of the airframe and/or structural component.

In a specific example, the composite material **110** may include aluminum and a plurality of CoNiAl particles embedded in the aluminum. The CoNiAl particles are present in the composite material **110** in an amount of about 10 parts by volume based on 100 parts by volume of the composite material **110**, so as to provide strain-sensing properties to the composite material **110**. Further, at least one of the CoNiAl particles changes crystallographic phase from austenite to martensite and changes magnetic phase upon exposure to the predefined critical macroscopic average strain ϵ_c applied at a temperature, T, of greater than or equal to about the martensite start temperature, M_s , of the CoNiAl and less than about an austenite start temperature, A_s , of the CoNiAl. Further, the composite material **110** may not revert to austenite from martensite, and the CoNiAl may generate an acoustic emission in response to the predefined critical macroscopic average strain ϵ_c that is greater in magnitude than an acoustic emission of the aluminum.

Referring again to FIG. **3**, a composite material **10**, **110** for sensing the predefined critical macroscopic average strain ϵ_c in structural applications includes the structural material **12**. The composite material **10**, **110** also includes the shape-memory alloy **14** having a characteristic of generating a signal AE, PC in response to a martensitic transformation. The shape-memory alloy **14**, which may be the ferromagnetic shape-memory alloy **114**, is embedded in the structural material **12** so that a structural characteristic of the structural material **12**, e.g., a strength or ductility, is not adversely affected. That is, the presence of the shape-memory alloy **14** does not adversely affect the structural characteristic of the structural material **12**.

The shape-memory alloy **14** may be substantially chemically bonded to the structural material **12** when embedded in the structural material **12**. Further, a configuration of the shape-memory alloy **14** may influence a load transfer from the structural material **12** to the shape-memory alloy **14**. That is, the configuration of the shape-memory alloy **14** may influence how the load applied to the composite material **10**, **110** is transferred between the structural material **12** and the shape-memory alloy **14**. The configuration of the shape-memory alloy **14**, for example, may be at least one of ellipsoidal and crenulated in shape. Such shapes may optimize the load transfer from the structural material **12** to the

shape-memory alloy **14** to minimize cracking at boundaries between the structural material **12** and the shape-memory alloy **14**.

Referring generally to FIG. **3**, the shape-memory alloy **14** undergoes the martensitic transformation within the composite material **10**, **110** in response to the predefined critical macroscopic average strain ϵ_c of the composite material **10**, **110** to generate the signal AE, PC that is different from, e.g., of greater intensity than, the signal generatable from a material that is substantially free from the shape-memory alloy **14**. That is, the signal, e.g., the acoustic emission AE and/or the crystallographic or magnetic phase change PC, is different from any signal generatable from a composite or structural material that does not include the shape-memory alloy **14**. For example, the signal AE, PC may be greater in magnitude than any signal generatable from a composite or structural material that does not include the shape-memory alloy **14**. Therefore, the shape-memory alloy **14** generates, for example, the acoustic emission AE that is detectable in response to the predefined critical macroscopic average strain ϵ_c of the composite material **10**, **110**.

A method of forming the composite material **10**, **110** for sensing the predefined critical macroscopic average strain ϵ_c includes providing the structural material **12** in powder form. That is, the structural material **12** may be in the form of loose particles having an average size of from about 100 μm to about 1,400 μm formed by any suitable method. For example, the structural material **12** may be comminuted via milling or grinding to provide the powder form.

The method further includes providing the shape-memory alloy **14**, which may be the ferromagnetic shape-memory alloy **114**, having the austenite crystallographic phase. As set forth above, the shape-memory alloy **14** changes crystallographic phase from austenite to martensite in response to the predefined critical macroscopic average strain ϵ_c of the composite material **10**, **110**. By way of example, the shape-memory alloy **14** may be initially provided in the form of an ingot, a block, a wafer, or a disc having an initial crystallographic phase after emerging from an induction furnace. The shape-memory alloy **14** having the austenite crystallographic phase may then be provided by heat treating the shape-memory alloy **14** at a temperature of from about 1000° C. to about 1500° C., e.g., at about 1300° C., for from about 1 to about 4 hours to change the initial crystallographic phase to austenite. The shape-memory alloy **14** may then be water quenched to room temperature to provide the shape-memory alloy **14** having the austenite crystallographic phase.

The method further includes changing a size and shape of the shape-memory alloy **14** to thereby form the plurality of particles of the shape-memory alloy **14**. The size of the particles may be reduced and the shape of the particles may be changed by any suitable method. For example, changing a size and shape may include grinding the shape-memory alloy **14** to form the plurality of particles. In other examples, the size and shape of the shape-memory alloy **14** may be changed by splat-cooling, gas atomizing, pulverizing, and/or plasma spraying.

The method also includes combining the structural material **12** and the plurality of particles of the shape-memory alloy **14** at a temperature of from about 500° C. to about 700° C. to thereby form the composite material **10**, **110** including the plurality of particles embedded in the structural material **12**. More specifically, the structural material **12** in powder form and the plurality of particles of the shape-memory alloy **14** may be combined in any order to form a mixture. In one example, the mixture may be vacuum

11

hot pressed at a temperature of from about 500° C. to about 700° C. and a pressure of from about 10 ksi (kilopound per square inch) to about 20 ksi for from about 10 to about 20 minutes. More specifically, the mixture may be vacuum hot pressed in a suitable vacuum hot pressing apparatus at a temperature of about 625° C. and a pressure of about 15 ksi for about 15 minutes to form the composite material **10**, **110**.

In another example, the mixture may be hot rolled at a temperature of from about 100° C. to about 200° C. to form the composite material **10**, **110**. More specifically, the mixture of the structural material **12** and the plurality of particles of the shape-memory alloy **14** may be vacuum sealed in a stainless steel bag and heated to a temperature of about 150° C. The stainless steel bag containing the mixture may then be rolled by a roller of a suitable hot rolling apparatus to form the composite material **10**, **110**.

For the method, processing parameters set forth above such as pressures, temperatures, order of addition, and particle sizes may be selected to optimize a microstructure of the composite material **10**, **110**. For example, variations in the microstructure of the composite material **10**, **110** that can be influenced by the processing parameters include particle size of the structural material **12**, crystallographic phase formation within the structural material **12**, retention of the shape-memory behavior of the shape-memory alloy **14**, and chemical reaction or diffusion between the shape-memory alloy **14** and the structural material **12**.

The methods provide composite materials **10**, **110** that optimize existing nondestructive evaluation (NDE) techniques for detecting strain of airframes and/or components thereof. That is, the composite materials **10**, **110** allow proactive, rather than reactive, strain-detection. Additionally, the composite materials **10**, **110** allow for both ground-based and in-flight inspection. Therefore, the composite materials **10**, **110** minimize costly and time-consuming detailed inspections and down-time of airframes and structural components, and minimize premature component replacement. Further, the composite materials **10**, **110** minimize aircraft complexity and weight, and allow for detection of comparatively smaller strain at comparatively earlier stages of fatigue than existing composite or structural materials. The composite materials **10**, **110** may also reduce existing airframe design constraints, since physical access to each component of the airframe for strain-detection may no longer be necessary. Such reduced design constraints may allow for comparatively larger payloads, increased service life, and less restriction on mission requirements as compared to airframes formed from existing composite or structural materials.

In further embodiments of the present invention, the shape-memory (non-ferromagnetic or ferromagnetic) alloy **14**, **114** may be present in the composite material **10**, **110** in a form other than particles. For example, referring to FIG. 4, the shape-memory alloy **14**, **114** and structural material **12** can be in laminate form **40**, consisting of one or more layers of shape-memory alloy **14**, **114** and structural material **12**, or the shape-memory alloy **14**, **114** can be a coating **50** on the structural material **12**, as shown in FIG. 5. The coating **50** may be applied to the entire structural material **12** or to selected areas of interest such as regions of high strain concentration **60**, as shown in FIG. 6. Such configurations where local strains are elevated due to applied stress **62** include, but are not limited to, hole inside diameter, fillet, and notch regions as shown in FIG. 6. Each shape-memory alloy layer **14**, **114** may be chemically bonded, mechanically bonded, or vapor deposited onto one or more structural materials **12** to produce each laminate **40** or surface coating

12

50. Each shape-memory alloy layer **14**, **114** is at least about 1 nm in thickness with the total volume to be less than that of the structural material **12**.

While the best modes for carrying out the invention have been described in detail, those familiar with the art to which this invention relates will recognize various alternative designs and embodiments for practicing the invention within the scope of the appended claims.

What is claimed as new and desired to be secured by Letters Patent of the United States is:

1. A composite material comprising:

a structural material; and

a plurality of particles formed from a shape-memory alloy and embedded in said structural material such that the ductility of the structural material is not adversely affected;

wherein the composite material is configured such that when a crack forms in the composite material with a crack tip process zone at a tip of the crack and an adjacent region disposed adjacent to said crack tip process zone, such that when the crack tip process zone reaches one of the plurality of particles formed from the shape-memory alloy, said shape-memory alloy within said crack tip process zone changes crystallographic phase from austenite to martensite within said crack tip process zone in response to a predefined critical macroscopic average strain within said crack tip process zone, and wherein a strain in said adjacent region is below the predefined critical macroscopic average strain, and said shape-memory alloy within said adjacent region does not change crystallographic phase from austenite to martensite within said adjacent region; and

wherein said shape-memory alloy having a changed crystallographic phase from austenite to martensite does not revert to austenite from martensite upon removal of said predefined critical macroscopic average strain.

2. The composite material of claim 1, wherein said predefined critical macroscopic average strain occurs at a temperature of greater than or equal to about a martensite start temperature, M_s , of said shape-memory alloy and less than about an austenite start temperature, A_s , of said shape-memory alloy.

3. The composite material of claim 1, wherein said structural material is present in said composite material in an amount of at least 40 parts by volume based on 100 parts by volume of said composite material.

4. The composite material of claim 1, wherein said shape-memory alloy is present in said composite material in an amount of less than or equal to about 25 parts by volume based on 100 parts by volume of said composite material.

5. The composite material of claim 1, wherein said shape-memory alloy generates an acoustic emission in response to said predefined critical macroscopic average strain that is greater in magnitude than an acoustic emission of said structural material.

6. The composite material of claim 1, wherein said shape-memory alloy is substantially chemically bonded to said structural material.

7. The composite material of claim 1, wherein said shape-memory alloy is a ferromagnetic shape-memory alloy.

8. The composite material of claim 7, wherein said ferromagnetic shape-memory alloy changes magnetic state upon exposure to said predefined critical macroscopic average strain.

9. The composite material of claim 1, wherein said shape-memory alloy includes an element selected from the

13

group of cobalt, nickel, titanium, indium, manganese, iron, palladium, zinc, copper, silver, gold, cadmium, tin, silicon, platinum, gallium, and combinations thereof.

10. The composite material of claim 1, wherein said structural material is a metal.

11. The composite material of claim 10, wherein said structural material is aluminum.

12. The composite material of claim 1, wherein said composite material forms at least a portion of an airframe.

13. A composite material comprising:

a structural material; and

a plurality of particles formed from a ferromagnetic shape-memory alloy and embedded in said structural material such that the ductility of the structural material is not adversely affected;

wherein the composite material is configured such that when a crack forms in the composite material with a crack tip process zone at a tip of the crack and an adjacent region disposed adjacent to said crack tip process zone, such that when the crack tip process zone reaches one of the plurality of particles formed from the ferromagnetic shape-memory alloy, said ferromagnetic shape-memory alloy within said crack tip process zone changes crystallographic phase from austenite to martensite within said crack tip process zone and changes magnetic phase within said crack tip process zone in response to a predefined critical macroscopic average strain within said crack tip process zone, and wherein a strain in said adjacent region is below the predefined critical macroscopic average strain, and said ferromagnetic shape-memory alloy within said adjacent region does not change crystallographic phase from austenite to martensite within said adjacent region and does not change magnetic phase within said adjacent region; and wherein said ferromagnetic shape-memory alloy having a changed crystallographic phase from austenite to martensite does not revert to austenite from martensite upon removal of said predefined critical macroscopic average strain.

14. The composite material of claim 13, wherein said predefined critical macroscopic average strain occurs at a temperature of greater than or equal to about a martensite start temperature, M_s , of said ferromagnetic shape-memory alloy and less than about an austenite start temperature, A_s , of said ferromagnetic shape-memory alloy.

15. A composite material comprising:

a laminate structure including:

at least one layer formed from a structural material; and

a shape-memory alloy embedded in said structural material such that the ductility of the structural material is not adversely affected

wherein the composite material is configured such that when a crack forms in the structural material with a crack tip process zone at a tip of the crack, such that the shape memory alloy has a strained region disposed adjacent said crack tip process zone and an adjacent region disposed adjacent to said strained region, wherein when the crack tip process zone reaches the shape-memory alloy, said shape-memory alloy in said strained region changes crystallographic phase from austenite to martensite within said strained region in response to a predefined critical macroscopic average strain within said strained region, and wherein a strain in said adjacent region is below the predefined critical macroscopic average strain, and said shape-memory alloy in said adjacent

14

region does not change crystallographic phase from austenite to martensite within said adjacent region; and

wherein said shape-memory alloy having a changed crystallographic phase from austenite to martensite does not revert to austenite from martensite upon removal of said predefined critical macroscopic average strain.

16. The composite material of claim 15, wherein said predefined critical macroscopic average strain occurs at a temperature of greater than or equal to about a martensite start temperature, M_s , of said shape-memory alloy and less than about an austenite start temperature, A_s , of said shape-memory alloy.

17. The composite material of claim 15, wherein said shape-memory alloy generates an acoustic emission in response to said predefined critical macroscopic average strain that is greater in magnitude than an acoustic emission of said structural material.

18. The composite material of claim 15, wherein said shape-memory alloy is a ferromagnetic shape-memory alloy.

19. The composite material of claim 18, wherein said ferromagnetic shape-memory alloy changes magnetic state upon exposure to said predefined critical macroscopic average strain.

20. The composite material of claim 15, wherein said shape-memory alloy includes an element selected from the group of cobalt, nickel, titanium, indium, manganese, iron, palladium, zinc, copper, silver, gold, cadmium, tin, silicon, platinum, gallium, and combinations thereof.

21. The composite material of claim 15, wherein said structural material is a metal.

22. The composite material of claim 21, wherein said structural material is aluminum.

23. The composite material of claim 15, wherein said composite material forms at least a portion of an airframe.

24. A composite material comprising:

a structural material; and

a plurality of particles formed from a ferromagnetic shape-memory alloy and embedded in said structural material such that the ductility of the structural material is not adversely affected;

wherein the composite material is configured such that when a crack forms in the structural material with a crack tip process zone at a tip of the crack, and such that the shape memory alloy has a strained region disposed adjacent said crack tip process zone and an adjacent region disposed adjacent said strained region, wherein when the crack tip process zone reaches the shape memory alloy, said shape-memory alloy within said strained region changes crystallographic phase from austenite to martensite within said strained region in response to a predefined critical macroscopic average strain within said strained region, and wherein a strain in said adjacent region is below the predefined critical macroscopic average strain, and said shape-memory alloy within said adjacent region does not change crystallographic phase from austenite to martensite within said adjacent region;

wherein said shape-memory alloy having a changed crystallographic phase from austenite to martensite does not revert to austenite from martensite upon removal of said predefined critical macroscopic average strain;

wherein said predefined critical macroscopic average strain occurs at a temperature of greater than or equal to about a martensite start temperature, M_s , of said

15

shape-memory alloy and less than about an austenite start temperature, A_s , of said shape-memory alloy; and wherein said shape-memory alloy generates an acoustic emission in response to said predefined critical macroscopic average strain that is greater in magnitude than an acoustic emission of said structural material.

25. The composite material of claim 24, wherein said shape-memory alloy is a ferromagnetic shape-memory alloy.

26. The composite material of claim 25, wherein said ferromagnetic shape-memory alloy changes magnetic state upon exposure to said predefined critical macroscopic average strain.

27. The composite material of claim 24, wherein said shape-memory alloy includes an element selected from the group of cobalt, nickel, titanium, indium, manganese, iron, palladium, zinc, copper, silver, gold, cadmium, tin, silicon, platinum, gallium, and combinations thereof.

28. The composite material of claim 24, wherein said structural material is a metal.

29. The composite material of claim 28, wherein said structural material is aluminum.

30. The composite material of claim 24, wherein said composite material forms at least a portion of an airframe.

31. The composite material of claim 1, wherein each of said plurality of particles is at least one of ellipsoidal and crenulated to thereby transfer said predefined critical macroscopic average strain from said structural material to said shape-memory alloy.

32. The composite material of claim 1, wherein said shape-memory alloy generates an acoustic emission within

16

said crack tip process zone in response to said predetermined critical macroscopic average strain that is greater in magnitude than an acoustic emission of said structural material within said adjacent region.

33. The composite material of claim 15, wherein said shape-memory alloy generates an acoustic emission within said strained region in response to said predetermined critical macroscopic average strain that is greater in magnitude than an acoustic emission of said structural material within said adjacent region.

34. An assembly comprising a structural component formed at least partially from the composite material of claim 32, and an acoustic monitoring device connected to the assembly, wherein the acoustic monitoring device is configured to detect the acoustic emission of said shape memory alloy.

35. An assembly comprising a structural component formed at least partially from the composite material of claim 33, and an acoustic monitoring device connected to the assembly, wherein the acoustic monitoring device is configured to detect the acoustic emission of said shape memory alloy.

36. An assembly comprising a structural component formed at least partially from the composite material of claim 13, and a magnetic monitoring device connected to the assembly, wherein the magnetic monitoring device is configured to detect the change in magnetic phase of said ferromagnetic shape memory alloy.

* * * * *